



TIKKURILA
AKROSTOP
SEALING PAINT

- DESCRIPTION** Water-borne acrylate sealing paint. Prevents bleeding caused by nicotine, soot, liquid drawing ink and dried water stains.
- RECOMMENDED USES** Wall and ceiling surfaces in interior spaces.
- PRODUCT FEATURES** For interior painting according to the directions for use, on objects at risk of bleeding. Suitable for new and previously painted concrete, plaster, brick, filler, chipboard, cardboard-covered gypsum board, wood, paneled, log and woodfiber board surfaces. Not suitable for painting iron or steel surfaces. Does not prevent the bleeding of wood extractives. Do not mix the product with other products.



AKROSTOP

TECHNICAL DATA

Colour Shades	Tinted white
Gloss	Full matt. 6/RT-classification
Coverage	6–8 m ² /l depending on the substrate.
Can sizes	1 l, 3 l, 10 l
Application method	Brush, roller or airless spray – nozzle 0.015–0.019" – thinning 0–10 vol-%
Drying time	Dust-dry in 1 h. Second coat 6 h. Recoatable in 24 hours.
Density (kg/l)	Approx. 1.3 kg/l, ISO 2811
Chemical resistance	Resistant to cleaning chemicals and mild solvents, such as white spirit.
Wet scrub resistance	SFS-EN 13300 class II, ISO 11998
Heat resistance	85 °C, ISO 4211-3.
Volume solids (%)	41
VOC	(cat A/g) 30 g/l (2010). Akrostop contains VOC max. 30 g/l
Storage	Protect from frost. Badly closed or short cans endure badly long-time storage.



AKROSTOP

APPLICATION INSTRUCTIONS

Application conditions

During painting and drying, the temperature of the air, surface and paint must be over +10°C and the relative humidity of the air below 80%.

Surface preparation

Clean the surfaces by removing any dirt and dust. Wash the surface with Maalipesu according to the instructions on the label. Fill holes and cracks with a suitable Tikkurila Presto or Prestonit filler and sand the dry surface. Remove the sanding dust.

Painting

Stir the paint well before use. Apply 1-2 coats by brush, roller or spray gun. Let the paint dry before next layer. Finish with a suitable finishing coat.

Cleaning of tools

Clean tools with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

The surface can be cleaned in approx. 1 month from painting if needed.

Clean the surfaces with a well-squeezed, damp soft sponge or cleaning cloth and a neutral (pH 6–8) washing solution. Follow the dilution instructions given by the detergent manufacturer when mixing the cleaning solution. The surface must not remain wet after cleaning.

After the surface treatment, the surfaces must be handled with care for a few weeks as the product achieves its final hardness and durability after about one month under normal conditions. If the surfaces need to be cleaned soon after surface treatment, clean them lightly with a damp cleaning cloth.

Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT). May produce an allergic reaction.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.