

Akvi Color AT-S

DESCRIPTION	A water-borne stain.				
PRODUCT FEATURES AND RECOMMENDED USES	 A water-borne stain with UV and sunlight resistant pigments. The stained wood will retain its color considerably longer. The product is designed for interior use. Can be used in Nordic Swan Ecolabeled buildings. As a water-borne product, it does not harm the environment. Enhances the appearance of natural wood structure. Due to the wide range of colors, it is easy to make the end product more unique. Natural-looking color samples on wood available by request. Designed for spraying and dipping. The stain does not contain free formaldehyde and after drying it does not emit formaldehyde to the environment. Recommended for furniture, doors and other wood and wood fibre surfaces indoors 				
TECHNICAL DATA					
Volume solids	2–20%, depending on the color				
Weight solids	3–25%, depending on the color				
Specific gravity	0.99–1.1 kg/litre depending on the color.				
Recommended spreading amounts and theoretical coverage	10–20 m ² /I depending on the color. Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.				
Drying times	80 - 100 g/m²	+20°C	+50°C	+70°C	IRM
	Recoatable, after	30min	15min	10min	5min
	Drying and recoating tin humidity of the air and		d to the film thic	ckness, tempera	ture, the relative

Color shades Shades from the Akvicolor AT colour cards and several colours by request. The product belongs to the Akvi Tone -tinting system.



Akvi Color AT-S

APPLICATION INSTRUCTIONS

Surface preparation	Remove dust, loose particles and other impurities from the surface. Wood surfaces must be sanded with sandpaper P150–320. Sanding prior to the next application with sandpaper P240–400. All sanding dust must be removed.		
	Note! The roughness of the sandpaper also effects of shade.		
Recommended topcoats	Merit 20, Merit Zircon Extra 25, Merit 30, Merit 80, Luminol Clear 25, Akvidur 20, Akvilac FD 25, Akvilac FD-J 10, Akvilac FD-J 25, Akvilac FD-J 35, Akvilac FD 70.		
	Note! Different kind of topcoats might be changed the color shades.		
Application conditions	The surface to be treated has to be clean and dry. The moisture content of wood has to be below 20%. During application and drying temperature of the air, substrate and product must be over +18°C and relative humidity of the air below 70%. Good ventilation is required to ensure optimal result. Product can be dried with or without oven.		
Application	Stir the stain carefully before use. Different application methods may result in shade variations. The shade and hue of the stain should be verified before applying large surfaces.		
	For conventional spraying, the product is thinned approximately 0–10%. Recommended nozzle tip is 1.0 –1.4 mm and pressure 1–3 bar. Spray angle shall be chosen according to the shape of the object.		
	For dip coating the product is not thinned.		
Thinners	Water		
Cleaning of equipment	Water.		
VOC	The Volatile Organic Compounds amount is 100 g/l of stain.		
HEALTH AND SAFETY	Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oyj.		
	For industrial and professional use only.		

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.