



TIKKURILA BETOLUX SOLVENT-BORNE FLOOR PAINT / GLOSS

DESCRIPTION	Urethane alkyd paint.
RECOMMENDED USES	Concrete and wooden floors and stairs in residential, commercial and storage premises. Suitable for floors subjected to light mechanical and chemical stress.
PRODUCT FEATURES	For interior painting of concrete and wooden floors. Also suitable for the maintenance painting of floors previously treated with an alkyd or epoxy paint or lacquer.





BETOLUX

Base paintsA BASE, C BASEColour ShadesColor cards: Feel the Color, Feel the Color 2020. Symphory color system Can be tinted in large part of Tikkurila colors.GlossGloss.CoverageConcrete floors 7–9 m²/l. Wood surfaces 9–11 m²/l.Can sizesA BASE: 0.91, 2.71, 91, 181 C BASE: 0.91, 2.71, 91, 181Application methodBrush, roller or spray.Drying timeDust dry in 3–4 hours. Recoatable after approx. 24 hours. Dry to use after approx. one week. Hardens completely and reaches its final durability in approx. one month.Density (kg/l)Good, SFS 3755.Heat resistanceGood, SFS 3755.Heat resistance50VOCCat A/l) SO0g/l (2010). Betolux contains VOC max. 500 g/l.StorageUnaffected by cold storage or transportation.	TECHNICAL DATA	
Feel the Color, Feel the Color 2020. Symphony color system Can be tinted in large part of Tikkurila colors.GlossGloss.CoverageConcrete floors 7–9 m²/l. Wood surfaces 9–11 m²/l.Can sizesA BASE: 0.9 l, 2.7 l, 9 l, 18 l C BASE: 0.9 l, 2.7 l, 9 l, 18 lApplication methodBrush, roller or spray.Drying timeDust dry in 3–4 hours. Recoatable after approx. 24 hours. Dry to use after approx. one week. Hardens completely and reaches its final durability in approx. one month.Density (kg/l)approx. 1.0 –1.2 kg/l, ISO 2811Chemical resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/l) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Base paints	A BASE, C BASE
CoverageConcrete floors 7–9 m²/l. Wood surfaces 9–11 m²/l.Can sizesA BASE: 0.9 l, 2.7 l, 9 l, 18 l C BASE: 0.9 l, 2.7 l, 9 l, 18 lApplication methodBrush, roller or spray.Drying timeDust dry in 3–4 hours. Recoatable after approx. 24 hours. Dry to use after approx. one week. Hardens completely and reaches its final durability in approx. one month.Density (kg/l)approx. 1.0 –1.2 kg/l, ISO 2811Chemical resistanceGood resistance to greases. Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner.Wash resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Colour Shades	Feel the Color, Feel the Color 2020. Symphony color system
Can sizes A BASE: 0.9 , 2.7 , 9 , 18 C BASE: 0.9 , 2.7 , 9 , 18 Application method Brush, roller or spray. Drying time Dust dry in 3–4 hours. Recoatable after approx. 24 hours. Dry to use after approx. one week. Hardens completely and reaches its final durability in approx. one month. Density (kg/l) approx. 1.0 –1.2 kg/l, ISO 2811 Chemical resistance Good resistance to greases. Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner. Wash resistance Good, SFS 3755. Heat resistance 120°C, light colors turn yellow in high temperatures, SFS 3757. Volume solids (%) 50 VOC (cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Gloss	Gloss.
C BASE: 0.9 I, 2.7 I, 9 I, 18 IApplication methodBrush, roller or spray.Drying timeDust dry in 3–4 hours. Recoatable after approx. 24 hours. Dry to use after approx. one week. Hardens completely and reaches its final durability in approx. one month.Density (kg/l)approx. 1.0 – 1.2 kg/l, ISO 2811Chemical resistanceGood resistance to greases. Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner.Wash resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Coverage	Concrete floors 7–9 m²/l. Wood surfaces 9–11 m²/l.
Drying timeDust dry in 3–4 hours. Recoatable after approx. 24 hours. Dry to use after approx. one week. Hardens completely and reaches its final durability in approx. one month.Density (kg/l)approx. 1.0 – 1.2 kg/l, ISO 2811Chemical resistanceGood resistance to greases. Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner.Wash resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Can sizes	
one week. Hardens completely and reaches its final durability in approx. one month.Density (kg/l)approx. 1.0 – 1.2 kg/l, ISO 2811Chemical resistanceGood resistance to greases. Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner.Wash resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Application method	Brush, roller or spray.
Chemical resistanceGood resistance to greases. Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner.Wash resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Drying time	
resistant to strong solvents such as thinner.Wash resistanceGood, SFS 3755.Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Density (kg/l)	approx. 1.0 –1.2 kg/l, ISO 2811
Heat resistance120°C, light colors turn yellow in high temperatures, SFS 3757.Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Chemical resistance	-
Volume solids (%)50VOC(cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Wash resistance	Good, SFS 3755.
VOC (cat A/i) 500g/l (2010). Betolux contains VOC max. 500 g/l.	Heat resistance	120°C, light colors turn yellow in high temperatures, SFS 3757.
Betolux contains VOC max. 500 g/l.	Volume solids (%)	50
Storage Unaffected by cold storage or transportation.	VOC	
	Storage	Unaffected by cold storage or transportation.



BETOLUX

APPLICATION INSTRUCTIONS

Application conditions

The concrete surface must be dry and at least 4 weeks old. The relative humidity of the concrete should not exceed 97%. During treatment and drying, the temperature of the air, surface and paint must be over +5°C and the relative humidity of the air below 80%.

Surface preparation

Unpainted floor:

Concrete floors: Remove the laitance with a grinding machine. Remove the sanding dust.

Wooden floors: Remove all dirt, dust, grease and oil.

Previously painted floor:

Wash with Maalipesu cleaning agent and rinse carefully with water. Allow to dry. Remove old, loose paint. Sand the surfaces thoroughly and remove the sanding dust.

Application

First application:

Stir the paint well before use. Apply two coats with a brush, a roller or a spray gun. Thin 20–25% with White Spirit 1050 for the first coat. Recoatable after 24 hours with unthinned or slightly thinned paint.

Maintenance painting:

Surfaces previously painted with Betolux floor paint can be maintenance painted with Betolux or Betolux Akva floor paint. See Pretreatment: Previously painted floor.

Roughening:

Reduce the slipperiness of the painted surface by adding one 1/3 I container of Liukueste non-slip powder to 10 liters of unthinned Betolux paint. It is sufficient to stir by hand. The roughened paint should be used for the final two coats.

Apply the "non-slip" paint to the entire floor area or parts of it marked off with masking tape. With stairs, for example, you can add an anti-slip strip to the outer edge of each step.

Cleaning of tools

Clean tools with White Spirit 1050 or Tikkurila Pensselipesu (Tool Cleaner).

Maintenance instructions

The painted surface will reach its final wear and chemical resistance approx. 1 month after the surface treatment. Avoid cleaning during this time. Clean the surface with a brush, a mop or a dust cloth. Dirty surfaces can be cleaned with a cleaning tool and a neutral (pH 6–8) washing solution.

Maintenance treatment

Surfaces previously painted with Betolux floor paint can be maintenance painted with Betolux or Betolux Akva floor paint. See Pretreatment: Previously painted floors.



BETOLUX

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Contains: hydrocarbons, C9-C11, n-alkanes, isoalkanes, cyclics, <2% aromatics. **Warning.** Flammable liquid and vapor. May cause drowsiness or dizziness. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Avoid breathing vapor. Use only outdoors or in a well-ventilated area. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

