



TIKKURILA
FEELINGS EFFECT FINISH
TRANSLUCENT DECORATIVE WALL FINISH

DESCRIPTION Full-matt acrylate-based translucent effect paint.

RECOMMENDED USES Interior walls and ceilings in residential, commercial and storage buildings.

PRODUCT FEATURES Interior walls in rooms on surfaces which have been previously painted with Feelings Interior Paint. Not suitable for painting doors or furniture.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

FEELINGS EFFECT FINISH

TECHNICAL DATA	
Base paints	CAP BASE
Colour Shades	<p>Color cards: Symphony color system, Feel the color. Can be tinted in Tikkurila colors. The final colour of the Feelings Effect Paint will depend upon the colour of the Feelings Interior Paint used as the basecoat.</p>
Gloss	Full matt.
Coverage	13-18 m ² /l. depending on application method. The above should be used as a guide, as actual spreading rates will depend upon many factors including texture and porosity of the substrate.
Can sizes	0.9 l
Thinner	Water
Application method	Brush or roller application. Finishing with effect roller, brush or other patterning tool.
Drying time (23°C and 50% relative air humidity)	Touch-dry after 12 hours. Recoatable after approx. 1 day.
Density (kg/l)	approx. 1.0 kg/l
Wash resistance	Withstands wiping with a damp cloth.
Heat resistance	85 °C, ISO 4211-3.
Volume solids (%)	12
VOC	<p>(cat A/I) 200g/l(2010) Feelings Effect Finish contains VOC max. 200 g/l.</p>
Storage	Protect from frost

FEELINGS EFFECT FINISH

APPLICATION INSTRUCTIONS

Application conditions

All surfaces to be painted must be dry, the temperature of the air above +10°C, and the relative humidity of the air between 30 and 70%.

Surface preparation

Surfaces must be clean, dry, and free from grease, dirt, oil, wax, all loose material and surface contamination. Use recommended Tikkurila products as cleaning agents and for mould removal. Use recommended Tikkurila fillers for filling cracks, nail holes, blemishes, etc., and leveling of uneven surfaces. Ensure that existing glossy, gloss painted and filled surfaces are thoroughly flattened down. Ensure that all surfaces are thoroughly prepared.

Priming

Prime unpainted walls with Feelings Universal Primer. Paint with Feelings Interior Paint 2 times. Paint previously painted walls 1-2 times to the desired colour with Feelings Interior Paint.

Stir the can thoroughly and apply one coat of Feelings Effect Finish evenly. Finish immediately by using a roller, brush or sponge working in approximately 1 metre strips. When a more translucent end result is required, thin the product by 5-10 % with water.

Cleaning of tools

Remove excess paint/ lacquer from tools and clean with water. Tikkurila Pensselipesu (Tool Cleaner) is recommended to be used to remove a bit hardened paint.

Maintenance instructions

At the earliest after approx. one month after painting the surfaces can be cleaned with dry brush or dust towel, if needed. Clean soiled surfaces with a neutral (pH 6-8) detergent solution using a damp cleaning cloth. Rinse and dry immediately after treatment. Follow manufacturer's instruction when diluting the detergent.

After treatment, handle the surface with care for a few weeks. Surface reaches its final hardness and durability in approx. 1 month under normal circumstances. If cleaning is needed soon after treatment, clean surface lightly with a dry or damp cleaning cloth.

Maintenance treatment

Maintenance painting:
Apply Feelings Interior Paint.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.