



TIKKURILA

# FINNGARD SILICONE PROTECT

## DESCRIPTION

Waterborne, silicone facade paint. For use on traditional lime-cement and cement plasters, mineral plasters thin-film polymer, acrylic and concrete surfaces. Can be used for renovation of dispersion and mineral (silicate) surfaces.

## RECOMMENDED USES

Especially recommended for renovation of thermal insulation systems made of expanded polystyrene and mineral wool.

## PRODUCT FEATURES

- Create hydrophobic surface with low water absorption, ensuring high durability
- Vapor permeable – allows moisture to be drained from the wall
- Surface highly resistant to fungi, molds and algae
- Resistant to dirt
- Available in a wide range of colors from Tikkurila Facade 760 color card

# FINNGARD SILICONE PROTECT

## TECHNICAL DATA

<b>Base paints</b>	AP BASE, C BASE
<b>Colour Shades</b>	<p><b>Color cards:</b> Tikkurila Finngard Silicone Protect colours, Facade 760 colour collection. Base AP and C.</p> <p>The colors from the Tikkurila "Facade" colour card and selected colors from the NCS and RAL. It is recommended to perform the appropriate color sample on the area. 1-2 m<sup>2</sup>. When choosing colors for facades, especially those exposed to intense sunlight, which can significantly heat up the surface recommend the use of color with a higher reflectance. We recommend the use of color whose reflectivity is greater than 40%. Light reflectance values are given in the Tikkurila FACADE 760 colour card.</p>
<b>Gloss</b>	Full matt.
<b>Coverage</b>	6-9 m <sup>2</sup> /l per one coat, depending on the absorbency and structure of the substrate, application method and painting tool used. Attempt to determine the performance for a given substrate. Make test painting in order to determine the coverage of the substrate.
<b>Can sizes</b>	<p>AP BASE: 0.9 l, 2.7 l, 9 l C BASE: 0.9 l, 2.7 l, 9 l FACTORY READYMADE SHADE: 2.7 l, 9 l</p>
<b>Application method</b>	Roller, spray or brush.
<b>Drying time</b>	In temp. +23 ±2°C, and relative air humidity 50 ±5%, the surface is dry after up to 3 hours. Apply next coat after min. 12 hours. The drying times and recoating depends on film thickness, temperature, relative humidity during painting.
<b>Density (kg/l)</b>	Approx. 1,5kg/l acc. EN ISO 2811-1:2012P
<b>Water vapour resistance (EN ISO 7783)</b>	V2 EN ISO 7783-2:2001P
<b>Water permeability (EN 1062-3)</b>	W3 EN 1062-3:2008P
<b>Permeability to CO<sub>2</sub> (EN 1062-6)</b>	C0 EN 1062-6:2003P
<b>Volume solids (%)</b>	60

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

# FINNGARD SILICONE PROTECT

<b>Average wall thickness</b>	E250<E2=<100, wg PN-EN 1062-1:2005P
<b>Grain size</b>	S1 drobne, wg PN-EN ISO 1524:2013:06E
<b>VOC</b>	Cat. A/c. Admissible content of VOC since 2010 – 40 g/l. The product includes less than 40 g/ l of VOC.
<b>Storage</b>	Protect from frost. Store and transport in tightly closed containers at temperatures between +5°C and +25°C. The product should be transported and stored in containers protecting against weather in temperature between +5°C to +25°C.

# FINNGARD SILICONE PROTECT

## APPLICATION INSTRUCTIONS

### Application conditions

Work at air and substrate temp. not lower than +5°C and not higher than +25°C. Avoid direct sunlight, relative humidity > 80%, rain and frost. Protect the paint coating from rain for min. 48 hours - the optimum temperature and humidity conditions (temperature +20°C, relative humidity below 55%). This interval under conditions of elevated humidity and lower temperatures of air and ground may be extended.

### Surface preparation

The substrate must be carrying, dry and clean. Humidity of painted substrates should not exceed 4%. Products can be applied min. 16 hours after priming with Tikkurila Finngard Uni Primer. The product is suitable for use in commercial form, and before use requires careful mixing, if necessary thin the paint max. up to 5%. Apply two coats in min. 12 hours intervals. In order to avoid streaking and discoloration apply the paint in continuously way. Technological breaks schedule at the edges of the walls. Provide adequate amount of paint from one production batch. The paint from different batches should be mixed before use. Do not apply on lime coatings and distemper paint.

#### Raw surfaces:

The surfaces of new cement-lime, cement and concrete seasoned min. 4 weeks. Remove loose parts of the ground, dirt, greasy stains and salt efflorescence. Remove algae, lichens and fungi. Wash the facade with water at high pressure. Unevenness and cracks equalize with mortar with composition similar to the original. Prime the surface with Tikkurila Finngard Uni Primer.

#### Previously painted surfaces:

Remove loose and loose material substrate, peeling paint, dirt, greasy stains and salt efflorescence. Wash the facade with water at high pressure. Permanently remove algae, lichens and fungi. Remove the chalky substrate (eg. by blasting). Unevenness and cracks equalize with mortar with composition similar to the original. Prime the surface with Tikkurila Finngard Uni Primer. Before the renovation of old coatings should be performed test application that will assess the adhesion of the new paint to the painted surface, eg. by cross-cut and allow for evaluation of the appearance and color of the coating. A positive result determines the use of the product.

### Priming

Surface should be primed by Finngard Uni Primer.

### Top coating

Apply system: primer + facade paint by Tikkurila brand. Do not apply on horizontal surfaces exposed to direct contact with weather conditions: rain, snow. The manufacturer is not responsible for poor quality coating in case when above instructions are disregarded. It is recommended to use ANZA painting tools.

### Cleaning of tools

Clean tools with water immediately after use. Remove as much paint as possible from painting tools before cleaning.

### Environmental protection and waste disposal

Liquid waste should be destroyed according to the local regulations for hazardous waste. Empty cans as well as cans with liquid waste should be taken to a disposal according to the local regulations. For more information please contact local authority. Do not pour liquid waste into drains.

### Health and Safety

**Contains:** 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)), 2-octyl-2H-isothiazol-3-one (OIT), 4,5-dichloro-2-octyl-2H-isothiazol-3-one (DCOIT). **Warning.** Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Avoid breathing mist/spray. Use only outdoors or in a well-ventilated area. Wear protective gloves. IF ON SKIN: Wash with plenty of soap and water. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. **Warning!**

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

## FINNGARD SILICONE PROTECT


Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. This paint contains a biocidal product for the preservation of the dry film. Contains 2-octyl-2H-isothiazol-3-one (OIT), 4,5-dichloro-2-octyl-2H-isothiazol-3-one (DCOIT) and 3-iodo-2-propynyl butylcarbamate (IPBC). This product contains a biocidal product for the preservation of the product during storage. Contains reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)) and 1,2-benzisothiazol-3(2H)-one (BIT).



GHS07

# FINNGARD SILICONE PROTECT

EN 1504-2:2004

	
Tikkurila Polska S.A. ul. Mościckiego 23 39-200 Dębica, Polska	
18	
TIK-PL\1\FSP\2018	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.