



Fontefire WF

DESCRIPTION

Water-borne intumescent coating with highest possible fire retardant properties on wood. When subjected to heat, Fontefire WF expands and forms an insulating layer of foam.

PRODUCT FEATURES AND RECOMMENDED USES

- The product has fire reaction class B-s1, d0, according to the standard EN 13501-1:2007+A1:2009, the highest possible for wood material
- Can be used on interior panels as part of fire protection paint systems
- Contains fungicides and can be used directly on the wood surface, protecting the paint film against mold, algae and other microbes. A separate wood preservative is not needed, which results in savings in production costs
- To be used as a fire retardant paint on interior wood, fibreboard, chipboard and plywood surfaces in industrial painting processes

TECHNICAL DATA

Volume solids 46±2%

Weight solids 54±2%

Specific gravity 1.24 kg / litre

Recommended spreading amounts and theoretical coverage

Recommended spreading amounts		Theoretical coverage
wet	dry	
350 g/m ²	130µm	3.5 m ² /l
380 g/m ²	140µm	3.3 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying times

	+50°C / RH 50%
Dust dry, after	5min
Touch dry, after	10min
Recoatable, after	1h

The product must be dried in oven.

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Paint film must be through dry prior to next painting. Ensure proper drying with tape test.

Gloss Matt.

Color shades Light grey.

Fontefire WF

APPLICATION INSTRUCTIONS

Surface preparation	Remove dirt and dust from the surface. Note: The product is intended to be used onto dry new wood surfaces. For industrial use only.
Recommended topcoats	Akvi Top DS 25 (100 g/m ²). Topcoating and assembling on-site: please contact Tikkurila Technical Service.
Application conditions	The surface to be treated has to be dry. Moisture content of wood has to be below 15% for interior wood. During application the temperature of the air, surface and paint has to be over +15°C and the relative humidity of the air between 20–60%.
Application	Stir the paint carefully before use. Avoid high speed stirring. Avoid making foam. Interior wood surfaces: Use 350 g/m ² wet paint, recommended film thickness/layer 175 g/m ² . Vacuum application according to manufacturer's instructions. For airless spraying, the product is not thinned. Recommended nozzle tip is 0.015"–0.026" and pressure min. 60–80 bar. Spray angle shall be chosen according to the shape of the object. For air-assisted airless spraying, the product is not thinned. Recommended nozzle tip is 0.013"–0.015" and pressure 40–80 bar. Atomizing air pressure should be 1–3 bar. Spray angle shall be chosen according to the shape of the object. For brush machine application, the product is not thinned. Wood contains resin and other colouring extractives especially in knots. Temperature and humidity fluctuations may cause paint coat discolouration in these areas.
Packing	Stacking temperature of the painted objects should be below +30°C. Isolating foam should be used on stacking ready painted wood panels.
Thinners	Water
Cleaning of equipment	Water.
VOC	The Volatile Organic Compounds amount is 19 g/litre of paint.

HEALTH AND SAFETY Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.
A health and safety data sheet is available on request from Tikkurila Oyj.

For industrial use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.