



Fontefloor Pu Cem Cove

DESCRIPTION A solvent-free, water-borne hybrid polyurethane concrete coving material.

PRODUCT FEATURES AND RECOMMENDED USES

- Fast curing coving material
- To be used with Fontefloor PU Cem systems
- Low odour

TECHNICAL DATA

Volume solids 100%

Specific gravity 1.75 kg / l (mixture)

Mixing ratio

Fontefloor PU Cem Cove mixture	Fontefloor PU Cem Cove A 0.6KG
	Fontefloor PU Cem B 0.62KG
	Fontefloor PU Cem C 8.78KG

Pot life (+23°C) At +20°C: approx. 15 minutes

Practical coverage For a flat substrate:

Approximately 2.4 metres/unit with a radius of 2 cm and 10 cm height
or
approximately 1 m² with a thickness of 5 mm/unit of 10 kg.

Note: maximum thickness of one layer is approx. 6 mm.

Practical coverage depends on the evenness of the substrate.

Drying time (+23°C) Foot traffic after 8 hours
Mechanical exposure after 24 hours
Chemical resistance after 7 days

At lower temperature the curing process will last longer.

Cleaning of equipment Cleaning of equipment with Thinner 1061. Equipment should be cleaned immediately after use before the primer has dried.

Finish Matt. Sunlight will affect on the shade and the gloss of the varnish in the long run.

Colors Red, green, buff, grey and crème.

Thinning instructions Do not thin Fontefloor PU Cem Cove.

VOC VOC 2004/42/EC (cat A/j) 140 g/l (2010)
Fontefloor PU Cem Cove: max. VOC < 140 g/l

Can sizes 1,5 L

Fontefloor Pu Cem Cove

APPLICATION INSTRUCTIONS

- Surface preparation** Always remove all grease, oil, and other impurities with Maalipesu detergent before grinding. Remove laitance or old peeling paint layers by power grinding, milling, or vacuum grit blasting. Choose the method best suited for the premises. Clean out pot holes removing all loose or brittle material. Open cracks with e.g. an abrasive tool. After mechanical pre-treatment remove all loose material and dust carefully with a vacuum cleaner.
The substrate must have a tensile strength above 1.5 MPa. For application on cementitious leveling screed: check compatibility with the leveling screed manufacturer.
- Application conditions** The relative humidity of the concrete should not exceed 97%. Residual moisture content should be below 4 weight-%. The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 80%.
- Mixing components** Mix the correct proportions of parts A and B thoroughly approx. 30 s by using a hand drill with a paddle, concrete mixer or power mixer. Add part C to the mixture and mix approx. 3 min until the mixture is homogenous. Ensure that the mixture is homogenous and use it immediately after mixing.

Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the screed and risk the success of the application.
- Priming** Prime with unthinned Fontefloor PU Cem Primer. Pour the mixture onto the floor, apply with a consumption of ± 0.25 kg/m².
- Patching** Patch pot-holes and cracks with unthinned Fontefloor PU Cem 2 or Temafloor 400 epoxy varnish and dry, clean sand. Mixing ratio e.g. 1 part by volume of epoxy or Fontefloor PU Cem 2 mixture and 1–2 parts by volume of sand of grain size \varnothing 0.1–0.6 mm. Sand the patched areas before overcoating, if necessary.
- Topcoating** Fontefloor PU Cem Cove is applied onto the uncured Fontefloor PU Cem Primer.
- Storage** Under cover and free of the ground, in dry conditions above +5°C and below +25°C. This is particularly important for the part C. Protect from frost even during transport.

- HEALTH AND SAFETY** Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.
A health and safety data sheet is available on request from Tikkurila Oyj.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.