



TIKKURILA

## LASSEN PUNAMAALI



- DESCRIPTION** Linseed-oil-based, water-borne red paint. The pigments used include weather-resistant iron oxides. Punamaali forms a breathable surface that wears out gradually over the years.
- RECOMMENDED USES** For the exterior sawn board or rough log walls of outbuildings.
- PRODUCT FEATURES** For painting exterior sawn board and rough log surfaces, whether new or previously painted with Swedish red paint or similar outbuilding paints.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



TIKKURILA

## LASSEN PUNAMAALI

### TECHNICAL DATA

<b>Colour Shades</b>	Red
<b>Gloss</b>	Full matt. (6/RT classification)
<b>Coverage</b>	For sawn board and rough log surfaces, 4–6 m <sup>2</sup> /l.
<b>Can sizes</b>	10 l
<b>Thinner</b>	Water
<b>Application method</b>	Application with a brush.
<b>Drying time (23°C and 50% relative air humidity)</b>	Dries in 4 hours. Apply the second coat after one day.
<b>Density (kg/l)</b>	1.2 kg/l, ISO 2811.
<b>Weather resistance</b>	Good also in industrial environment.
<b>Volume solids (%)</b>	17
<b>VOC</b>	(cat A/d) max. 130g/l (2010). Lassen Punamaali contains VOC max. 130g/l.
<b>Storage</b>	Protect from frost.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

# LASSEN PUNAMAALI

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be painted must be dry, the temperature of the surface and air at least +5 °C and the relative humidity of the air below 80 % during painting and drying.

### Surface preparation

Unpainted surfaces:

Brush the wood surface clean of dirt, dust and loose wood fibers. Remove loose resin from knots with a steel trowel. Protect any metal parts prone to rust with Rostex Super anti-corrosion primer.

Previously painted surfaces:

Remove as much paint as you can from surfaces painted with Swedish red paint or a similar outbuilding paint with a wire brush and brush the surface clean with a dusting brush. Protect any metal parts prone to rust with Rostex Super anti-corrosion primer.

### Painting

Stir the paint well before and during use and thin it with water if necessary. Apply one or two generous coats with a brush. To achieve a uniform tone for the surface, mix a sufficient amount of paint in a single container.

### Cleaning of tools

Clean tools immediately after use with water.

### Maintenance instructions

Handle the painted surface with care. If the surface gets dirty, it can be brushed lightly or washed without detergents.

### Environmental and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

### HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)) and 3-iodo-2-propynyl butylcarbamate (IPBC). May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.