



TIKKURILA

LUJA 40

EXTRA DURABLE FINISH, SEMI-GLOSS**DESCRIPTION**


Special acrylic paint. The product contains an anti-mold agent that protects the paintwork.

RECOMMENDED USES

Interior walls and ceilings in spaces in which high wash and wear resistance is required, such as lobbies, stairwells, hospital corridors, patient rooms and other surfaces which are subjected to higher than normal stress. The product is approved for indirect contact with food (Finnish Food Act 23/2006).

PRODUCT FEATURES

For interior painting of concrete, plaster, filler-treated, brick, chipboard, plasterboard and wood fiberboard surfaces. Suitable for both new and previously painted surfaces.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

LUJA 40

TECHNICAL DATA	
Base paints	A BASE, C BASE
Colour Shades	Color cards: Feel the Color, Symphony Color System, Deco Grey colour card, Deco Grey Opaques, Feel the Color 2020. Can be tinted in Tikkurila colors.
Gloss	Semi-gloss. 3/RT-classification
Coverage	Theoretical coverage: 8 m ² /l. Practical coverage depends on the application method, conditions, shape and roughness of the surface to be treated.
Can sizes	A BASE: 0.9 l, 2.7 l, 9 l, 18 l C BASE: 0.9 l, 2.7 l, 9 l
Application method	Brush, roller or airless spraying – nozzle 0.015"–0.021" – thinning 0–5% by volume
Drying time	Touch-dry after approx. 2 hours. Recoatable after approx. 4 hours.
Density (kg/l)	Approx. 1,2 kg/l, ISO 2811
Chemical resistance	Resistant to white spirit and other solvents.
Wash resistance	Very good. Can also be washed with detergents and disinfectants used in hospitals.
Wet scrub resistance	SFS-EN 13300 class I, ISO 11998
Heat resistance	85 °C, ISO 4211-2 and ISO 4211-3
Volume solids (%)	40
Storage	Protect from frost. Badly closed or short cans and/or tinted products do not withstand long storage. Tinted products should be used during the same painting season.



LUJA 40

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry, the ambient temperature at least +5 °C and the relative humidity of air below 80%.

Surface preparation

Unpainted surfaces:

Clean the new surfaces by removing any dirt and dust. If necessary, level the surfaces with a suitable Presto filler and sand the dried surface. Remove the sanding dust. Prime with Luja Universal Primer, Ykköspohja primer or Varma Primer.

Previously painted surfaces:

Wash the previously painted surfaces with Maalipesu or Seinäpesu detergent according to instructions and let dry. Remove any loose, flaking paint with a scraper. Sand the painted surfaces non-glossy. Remove the sanding dust. Fill any holes and cracks and level the surfaces with a suitable Presto filler. Sand the filler and remove the sanding dust. If necessary, prime with Luja Yleispohjamaali, Ykköspohja or Varma primer before finishing.

Painting

Stir Luja finishing paint well before use. Apply 1-2 coats by roller, brush or spray.

Cleaning of tools

Clean tools with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

If needed, after approx. 1 month from treating the surface, at the earliest. Clean the surfaces with a neutral (pH 6–8) cleaning solution and e.g. a soft brush, sponge or cleaning cloth. Clean very dirty surfaces with a mild alkaline (pH 8–10) cleaning solution and e.g. a cleaning cloth or sponge.

After cleaning, rinse the surfaces thoroughly. Follow the dilution instructions given by the detergent manufacturer when mixing the cleaning solution. After the surface treatment, the surfaces must be handled with care for a few weeks, as the product will reach its final hardness and durability in about one month under normal conditions. If the surfaces need cleaning soon after the surface treatment, clean them lightly by using a soft brush or a damp cloth.

Maintenance treatment

Surfaces painted with Luja finishing paint can be maintenance painted with a same or similar water-borne paint. See Pretreatment.

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Harmful to aquatic life with long lasting effects. Avoid release to the environment. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Contains 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)) and 2-octyl-2H-isothiazol-3-one (OIT). May produce an allergic reaction. This paint contains a biocidal product for the preservation of the dry film. Contains OIT. This product contains a biocidal product for the preservation of the product during storage. Contains C(M)IT/MIT (3:1). Wear protective gloves.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.