



TIKKURILA

# MULTISTOP

**EFFECTIVE ISOLATING PRIMER FOR WOODEN SURFACES****DESCRIPTION**

Sealing primer for the prevention of discoloration on interior wooden surfaces.

**RECOMMENDED USES**

Ceiling and wall panels, wooden floors, skirting, doors, windows and furniture.

**PRODUCT FEATURES**

Suitable as primer and intermediate coat for both untreated and previously painted or varnished, new or old wood surfaces in dry interior premises. Prevents discoloring wood extracts and other yellowing substances such as tar, etc. from entering into the top coat. Prevents discoloration caused by wood knots. Also suitable for bathroom panel ceilings when the surface is finished with Luja top coat.



# MULTISTOP

TECHNICAL DATA	
<b>Colour Shades</b>	White F497
<b>Gloss</b>	Matt.
<b>Coverage</b>	approx. 7 m <sup>2</sup> /l (minimum amount to be applied 260 g/m <sup>2</sup> , wet film thickness 200 µm, dry film thickness 75 µm)
<b>Can sizes</b>	1 l, 3 l, 10 l
<b>Application method</b>	Brush, roller or spray gun. Airless spray nozzle 0.013", no thinning.
<b>Drying time</b>	Touch-dry after approx. one hour. Recoatable the following day.
<b>Density (kg/l)</b>	1.3 kg/l, ISO 2811
<b>Volume solids (%)</b>	41
<b>VOC</b>	(cat A/a) 30g/l(2010) Multistop contains VOC max. 30 g/l
<b>Storage</b>	Protect from frost.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

# MULTISTOP

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be painted must be dry, the temperature at least +10°C, and the relative humidity of the air less than 80 %. A low temperature (approx. +15°C) and higher humidity (50–70 % RH) will extend the working time and make application easier.

### Surface preparation

#### Untreated surfaces:

In order to ensure the best possible adhesion, clean new wooden surfaces from any dirt and dust.

#### Previously treated surfaces:

Wash previously painted or lacquered surfaces with Maalipesu according to need. To remove any wax containing washing solution wash floors with Maalipesu cleaning agent diluted with water to a ratio 1:5. Rinse the detergent residue carefully out. Allow to dry. Remove loose paint or lacquer and sand the whole surface. Sand especially floors carefully matt. Remove sanding dust.

If necessary, use Presto Rapid Filler or Helmi Furniture Filler to fill any cracks and dents. The small dents on the floors can be filled with Spakkeli Wood Filler. Sand the filled areas and remove the sanding dust. Patch paint with primer on bare wood surfaces.

### Application

Stir Multistop well before use. The product is used undiluted. Spread amply 1-2 times, preferably with a roller and even out immediately with an artificial fiber brush. The best result is achieved with two applications. Let dry until the next day before the second coating. This way it is better shielded against strike throughs.

Finish panel ceilings with Paneelikatto Valkoinen, panel walls with suitable Helmi Furniture Paint and floors with Betolux Akva or Pontti Puulattiamaalii. The roof surfaces can be left without the surface coating, as long as the treatment is performed twice.

### Cleaning of tools

Clean tools with water. Remove excess paint/ lacquer from tools and clean with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

### Maintenance instructions

After the surface treatment, surfaces must be handled with care for a few weeks, as the product will reach its final hardness and durability under normal conditions after about a month.

If required after one month from painting, but no earlier:

Clean the surface with neutral (pH 6–8) dish-washing liquid solution and a soft brush, sponge or cloth. Clean soiled surfaces with a mild alkaline (pH 8–10) detergent solution and, for example, a cloth, mop or sponge. Rinse the surface carefully.

### Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

### Health and Safety

Wear protective gloves. Contains 2,4,7,9-Tetramethyldec-5-yne-4,7-diol and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.