



TIKKURILA
NASTA SEINÄMAALI



DESCRIPTION Water-borne matte paint for interiors.

RECOMMENDED USES Interior walls and ceilings on dry premises.

PRODUCT FEATURES For interior painting of concrete, plaster, filler-treated, plasterboard, chipboard and wood fiberboard surfaces according to instructions. Also suitable for repainting previously painted surfaces.



NASTA SEINÄMAALI

TECHNICAL DATA

Base paints	A BASE
Colour Shades	Light shades can be tinted in Tikkurila colors.
Gloss	Matt.
Coverage	Non-absorbent surfaces: 9–12 m ² /l. Absorbent surfaces: 6–9 m ² /l.
Can sizes	9 l
Application method	Roller, spray or brush. Airless spray application -nozzle 0.017"-0.021" -thinning 0-10% by volume.
Drying time (23°C and 50% relative air humidity)	Dust dry after approx. 30 minutes. Recoatable after 2 hours.
Density (kg/l)	1.3 kg/l, ISO 2811.
Wet scrub resistance	SFS-EN 13300 class II ISO 11998
Heat resistance	85 °C, ISO 4211-3.
Volume solids (%)	34
Storage	Protect from frost and direct sunlight. Badly closed or short cans endure badly long-time storage.



NASTA SEINÄMAALI

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry, the temperature at least +5°C and the relative humidity of the air below 80%.

Surface preparation

Unpainted surfaces:

Clean the surfaces by removing any dirt and dust. If necessary, level the surfaces with a suitable Tikkurila Presto filler and sand the dried surface. Remove the sanding dust. Prime with Nasta ceiling paint and primer.

Previously painted surfaces:

Wash previously painted surfaces with Seinäpesu cleaning agent. Sand the painted surfaces non-glossy. Remove the sanding dust. Fill cracks and holes with a suitable Tikkurila Presto filler and sand the dried surface. Remove the sanding dust. Prime unpainted surfaces with Nasta Primer and Ceiling paint.

Painting

Stir Nasta wall paint well before use and thin with water, if necessary. Apply 1–2 coats by roller, brush or spray.

Cleaning of tools

Clean tools with water. Remove excess paint/ lacquer from tools and clean with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

If needed, after approx. 1 month from treating the surface, at the earliest.

Surfaces can be cleaned with a dry brush or dust cloth. Any dirty surfaces can be cleaned with a neutral (pH 6–8) cleaning solution and a damp cleaning tool. The surface may not remain wet after cleaning. Follow the dilution instructions given by the detergent manufacturer when mixing the cleaning solution.

The product achieves its final hardness and durability after one month under normal conditions, and therefore the surfaces must be handled with care during this time. If the surfaces need to be cleaned soon after finishing, clean them lightly with a dry or damp cleaning cloth.

Maintenance treatment

Surfaces painted with Nasta wall paint can be maintenance painted with same or similar water-borne wall paints.

Environmental and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.