



TIKKURILA

ÖLJYPOHJAINEN PUNAMAALI

DESCRIPTION Linseed-oil-based, water-borne red paint. The pigments used include weather-resistant iron oxides. Punamaali forms a breathable surface that wears out gradually over the years.

RECOMMENDED USES Sawn boards and rough log surfaces.

PRODUCT FEATURES New outbuildings and properties previously painted with Swedish red paint.



ÖLJYPOHJAINEN PUNAMAALI

TECHNICAL DATA

Colour Shades	Tikkurilan Punamulta TVT 2691.
Gloss	Full matt.
Coverage	For sawn board and rough log surfaces, 4–6 m ² /l.
Can sizes	10 l
Application method	Application with a brush.
Drying time (23°C and 50% relative air humidity)	Dries in 4 hours. Apply the second coat after one day.
Density (kg/l)	1.2 kg/l, ISO 2811
Volume solids (%)	19
Storage	Protect from frost.



ÖLJYPOHJAINEN PUNAMAALI

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry, the temperature of the surface and air at least +5 °C and the relative humidity of the air below 80 % during painting and drying.

Surface preparation

Unpainted surfaces:

Brush the wood surface clean of dirt, dust and loose wood fibers. Remove loose resin from knots with a steel trowel. Protect any metal parts prone to rust with Rostex Super anti-corrosion primer.

Previously painted surfaces:

Remove as much paint as you can from surfaces painted with Swedish red paint or a similar outbuilding paint with a wire brush and brush the surface clean with a dusting brush. Protect any metal parts prone to rust with Rostex Super anti-corrosion primer.

Painting

Stir the paint well before and during use and thin it with water if necessary. Apply one or two generous coats with a brush. To achieve a uniform tone for the surface, mix a sufficient amount of paint in a single container.

If the product will be sprayed on, you should brush the surface tightly immediately after spraying in order to ensure the adhesion and correct thickness of the paint.

Cleaning of tools

Clean tools immediately after use with water.

Maintenance instructions

Handle the painted surface with care. If the surface gets dirty, it can be brushed lightly or washed without detergents.

Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)) and 3-iodo-2-propynyl butylcarbamate (IPBC). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains C(M)IT/MIT (3:1). Wear protective gloves.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.