



# TIKKURILA PETSILAKKA

|                         |  |
|-------------------------|--|
| <b>DESCRIPTION</b>      | Traditional tinted alkyd lacquer for interior wood surfaces. |
| <b>RECOMMENDED USES</b> | Furniture.   |
| <b>PRODUCT FEATURES</b> | Furniture.   |



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



TIKKURILA

## PETSILAKKA

| TECHNICAL DATA                                   |   |
|--|---|
| Paint product group 2012                         | 522 Irtokalusteiden liuteohenteiset lakat RL03...05   |
| Colour Shades                                    | Colors: oak, walnut, mahogany and black   |
| Gloss  | High gloss.   |
| Coverage   | 10-14 m <sup>2</sup> /l depending on the degree of darkness required.   |
| Can sizes  | 0.333 l, 1 l  |
| Application method                               | Brushing, spraying.   |
| Drying time (23°C and 50% relative air humidity) | Dust dry after 4 hours, dry to handle after 12 hours. Recoatable after 24 hours. The drying time is affected by the surface and the number of coats.                |
| Density (kg/l)                                   | 0.9 kg/l, ISO 2811.   |
| Chemical resistance                              | Resistant to white spirit and denatured alcohol. Not resistant to strong solvents such as thinner. Resists vegetable and animal fats, lubricating oils and greases. |
| Abrasion resistance                              | Good  |
| Wash resistance                                  | Great with all common detergents, SFS 3755.   |
| Volume solids (%)                                | 38  |

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



# PETSILAKKA

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be treated must be dry, the temperature at least +5°C and the relative humidity of the air below 80%.

### Surface preparation

New unvarnished surfaces:

Clean the surface of any dirt and dust.

Previously varnished surfaces:

Wash previously painted or lacquered surfaces with Maalipesu or Tehopesu detergent and rinse carefully with water. Remove the old lacquer by scraping, inasmuch as this is possible, and sand the entire surface. Remove the sanding dust.

### Lacquering

Stir the Petsilakka lacquer well before use. First carry out a trial lacquering to check the color of the lacquer on the surface to be treated. To ensure a smooth color, thin the lacquer with white spirit. Spread the thinned Petsilakka lacquer in one or more thin layers, depending on the degree of darkness desired. If the lacquer is too dark, it can be made lighter by adding colorless Unica Super or White Spirit 1050.

### Maintenance instructions

If needed, approx. 1 month after lacquering at the earliest: The surfaces are cleaned with a soft brush, sponge or cleaning cloth and neutral (pH 6-8) dish washing solution. Clean very dirty surfaces with a mild alkaline (pH 8-10) cleaning solution and e.g. a cleaning cloth, mop or sponge. Rinse the surface carefully.

The product achieves its final hardness and durability after one month under normal conditions, therefore the surfaces must be handled with care during a couple of weeks. If the surfaces need to be cleaned soon after finishing, clean them lightly with a soft brush, damp cleaning cloth or mop.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.