

Fontefloor EP-FD Primer

DESCRIPTION

A two-component fast drying pigmented waterborne epoxy primer

PRODUCT FEATURES AND RECOMMENDED USES

- Seals the concrete surface and ensures good adhesion for Tikkurila Fontefloor paints and Temafloor coatings.
- Fast drying.
- White pigmented.
- Good watervapour permeability.
- The M1 classification for low-emitting building materials has been granted by the Finnish Building Information Foundation RTS.
- Used for dust binding and priming of concrete floors.

TECHNICAL DATA

Volume solids

Approx. 41 %.

Specific gravity

1.1 kg / litre (mixture)

Mixing ratio

Base	2 parts by volume	Fontefloor EP-FD Primer
Hardener	1 part by volume	Fontefloor EP-FD Primer Hardener

Pot life (+23°C)

about 45 minutes in the mixing container.

Practical coverage

Coverage on concrete floors is on the average:
Priming 5-7 m²/l
The coverage depends on the porosity and evenness of the substrate and on the application method.

Drying time (+23°C)

Dust dry after 30 minutes
Recoat after 2 hours (waterborne and epoxy products)
Recoat after 6 hours (solvent free polyurethanes)
Fully cured after 7 days
At lower temperatures the curing process will last longer.

Application method

rubber trowel, roller

Thinners

Water

Cleaning of equipment

Water. Equipment should be cleaned immediately after use before the paint has dried.

Reaction to fire

Bfl -s1

VOC

VOC 2004/42/EC (cat A/j) 140 g/l (2010)
Fontefloor EP-FD Primer: max. VOC < 140 g/l

Can sizes

20,0 L

Fontefloor EP-FD Primer

APPLICATION INSTRUCTIONS

Surface preparation	<p>Always remove all grease, oil, and other impurities with Maalipesu detergent before grinding. Remove laitance or old paint layers by power grinding, milling, or vacuum grit blasting. Choose the method best suited for the premises.</p> <p>Clean out pot holes removing all loose or brittle material. Open cracks with e.g. an abrasive tool. After mechanical pre-treatment remove all loose material and dust carefully with a vacuum cleaner.</p> <p>The substrate must have a tensile strength above 1.5 MPa. For application on cementitious leveling screed: check compatibility with the leveling screed manufacturer</p>
Application conditions	<p>The relative humidity of the concrete should not exceed 97%. Residual moisture content should be below 4 weight-%.</p> <p>The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 80 %.</p>
Mixing components	<p>First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 3 minutes to get homogenous mixture) by using a low speed industrial hand drill with paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.</p>
Priming	<p>Prime using 20-30 % thinned Fontefloor EP-FD Primer. Always add the water needed to a ready mixture and stir thoroughly. Pour the mixture onto the floor, apply with a rubber trowel and level with a roller. Repeat priming to get a non-porous surface using 5-10 % thinned Fontefloor EP-FD Primer. A porous priming coat will result in holes and air bubbles in the finished coating.</p>
Patching	<p>Patch pot-holes and cracks with a mixture of unthinned Temafloor 400 and dry, clean sand. Mixing ratio e.g. 1 part by volume of varnish mixture and 1–2 parts by volume of sand of grain size 0.1–0.6 mm. Sand the patched areas before overcoating, if necessary.</p>
Topcoating	<p>Overcoating should be done within 2-48 hrs (6-48 hrs for solvent free polyurethanes) after priming. If the primed surface is not overcoated within 48 hrs, it should be abraded. Pour the mixture onto the floor and apply the top coat according to instructions given in the corresponding Product Data Sheet.</p> <p>Note! Add the remaining mixture to the next batch of the paint or screed, do not scrape it out of the container onto the floor.</p>

HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.</p> <p>A health and safety data sheet is available on request from Tikkurila Oyj.</p>
--------------------------	--

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

Fontefloor EP-FD Primer

EN1504-2:2004

The European harmonized product standard EN 1504-2:2004 defines the requirements for surface protection systems for concrete.

This product is tested and CE-labelled in accordance with the tables 1d and 1f in the appendix ZA.

CE	
0809	
Tikkurila Oyj Heidehofintie 2 FI-01300 Vantaa	
22	
TIK-A060-2021	
EN1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO ₂	SD > 50 m
Capillary absorption and permeability to water	w < 0,1 kg/m ² · h _{0,5}
Reaction to fire	Bfl -s1
Adhesion strength by pull off test	≥ 2,0 N/mm ²
Release of dangerous substances	NPD
Permeability to water vapour	Class I, SD < 5 m