



## TIKKURILA LASERA

- DESCRIPTION** Water-borne additive meant to be added to Tikkurila water-borne interior paints like Joker, Harmony, Luja, and Remontti-Ässä before decorative painting. Lasera makes the paint glazing and gives more working time. May weaken water-resistance of the base paint.
- RECOMMENDED USES** For interior walls and ceilings.
- PRODUCT FEATURES** For decorative painting indoors. Lasera gives easy, fast and safe way to apply decorative painting with various colour and pattern choices.



# LASERA

## TECHNICAL DATA

<b>Colour Shades</b>	Colorless.
<b>Coverage</b>	9 - 15 m <sup>2</sup> /l, mixture of Lasera and paint.
<b>Can sizes</b>	1 l
<b>Thinner</b>	Water
<b>Application method</b>	Apply by roller, make patterns by sponge, roller, brush or cloth.
<b>Drying time</b>	Normally dry after approx. 3 hours.
<b>Density (kg/l)</b>	1,0 kg/l, ISO 2811.
<b>Volume solids (%)</b>	4
<b>Storage</b>	Protect from frost

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



# LASERA

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be treated must be dry, the temperature of the air at least +5°C, and the relative humidity of the air below 80 %.

### Surface preparation

Clean dirt and dust from surfaces to be treated. Wash down previously painted surfaces with Maalipesu cleaning agent and rinse carefully with water. Prime steel surfaces with Rostex Super Akva metal primer. Fill surfaces with a suitable Presto filler, if necessary. Paint directly with a water-borne tinted Tikkurila paint e.g. Joker, Harmony or Luja.

### Application

Stir Lasera before use and add it to tinted paint in a ratio of 1:1 and stir well. Apply glazing paint by roller and make patterns right after with sponge, roller or cloth. Make patterns only for area about 1 square metre at a time and for larger areas about half a metre wide working bands.

Clean tools from time to time with water and squeeze dry. Apply first a test coat e.g. on cardboard.

### Cleaning of tools

Remove excess paint/ lacquer from tools and clean with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

### Maintenance instructions

Lasera reaches its final durability in approx. 1 month. Avoid cleansing during that time.

Clean soiled surfaces with a neutral (pH 6-8) dishwashing agent using a soft cleaning towel. Rinse and dry immediately after treatment. Follow manufacturer's instruction when diluting dishwashing agent.

After treatment, treat surface with care for a few weeks. Surface reaches its final hardness and durability in approx. 1 month under normal circumstances. If needed, clean surface with a soft brush, a damp rag or mop.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.