



TIKKURILA

MUURI NEW

PAINT FOR FIREPLACES AND FIREWALLS

DESCRIPTION

Silicate paint for interior use with excellent heat-resistance.

RECOMMENDED USES

Firewalls, fireplaces and similar interior wall surfaces where the surface temperature may rise above normal.

PRODUCT FEATURES

Concrete, lime, lime cement, cement plaster, sandlime brick and brick surfaces as well as mineral board surfaces indoors. Suitable also for surfaces previously painted with lime, lime cement, cement and silicate paints. See instructions.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

MUURI NEW

TECHNICAL DATA	
Base paints	KSA BASE
Colour Shades	Color cards: New Muuri fireplaces and firewalls colour collection 2025 KSA-base paint (white) can be used as such. Or can be tinted in different shades from Muuri color selection
Gloss	Full matt. 6/RT-classification
Coverage	4-6 m ² /l for one layer. Coverage is affected by the roughness and porosity of the surface as well as the application method and conditions.
Can sizes	0.9 l, 2.7 l
Thinner	water
Application method	Brush or limebrush
Drying time	Re-coatable after 12 hours.
Density (kg/l)	Approx. 1.4 kg/l, ISO 2811
Water vapour resistance (EN ISO 7783)	$s_{d,H_2O} < 0,14 \text{ m.}$
Heat resistance	180 °C dry heat
VOC	(cat A/a) 30g/l(2010). Muuri VOC amount is max. 30 g/l.
Storage	Protect from frost and direct sunlight. Close can carefully for next use. Badly closed or short cans and/or tinted products do not withstand long storage. Tinted products should be used during the same painting season.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



MUURI NEW

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be clean, dry and solid and the temperature of the air and surface at least +10 °C and the relative humidity of the air below 80 %.

Surface preparation

Unpainted surfaces:

New concrete, screed and plastered surface must be sufficiently dried and hardened before finishing treatment.

Clean unpainted surfaces from dirt, dust and other impurities.

Previously painted surfaces:

Clean surfaces from dirt, dust and other impurities. If necessary, clean with Tikkurila Seinäpesu Cleaning agent according to instructions. Remove flaking and poorly attached or powdery paint layers. Sand previously painted glossy surfaces to non-glossy.

Patching

Patch cracks, holes and dents so that they are level with the surrounding surface. Use an appropriate dry filler on concrete surfaces and lime plaster or lime cement plaster on plaster surfaces. If necessary, patch paint smoothed areas with Muuri paint.

Painting

Apply one priming coat of Muuri Fireplace paint. The product can be thinned with water up to 10%, if necessary. After the primer has set for at least 12 hours, finishing coat will be applied.

NOTE:

Cover surfaces that will not be treated, such as windows, natural stone or clinker-tiled surfaces and metal surfaces. Remove any paint spatter immediately with water.

The variable porous structure of the surface to be painted and moisture and temperature variations during paint application and drying may cause diversity of color.

Cleaning of tools

Clean tools with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

If necessary, clean the surfaces with a dry brush, mop or dust cloth after a month of the surface treatment at the earliest.

It is recommended to wait for at least two weeks before the treated surfaces are taken into use so that the product can reach the heat durability requirements set for it.

Mechanical strain may cause visible marks on the painted surface. This is a typical product feature of matt paints; however, it does not affect the technical functionality of the product.

Maintenance treatment

Surfaces painted with Muuri paint can be maintenance painted with the same product

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



MUURI NEW

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.