



TIKKURILA

NOVOFLOOR 1-K ELASTIC N

ONE-COMPONENT POLYURETHANE COATING

DESCRIPTION Elastic and hardened by air humidity, UV-resistant, low-solvent single component polyurethane floor coating.

RECOMMENDED USES For coating the floors of balconies, outdoor corridors, outdoor passenger corridors, etc.

PRODUCT FEATURES For floors with concrete and cement mortar surfaces that require flexibility, good water resistance and crack bridging. Particularly suitable for coating balconies. Not recommended for floors subjected to high mechanical stress.

For professional use only.





TIKKURILA

NOVOFLOOR 1-K ELASTIC N

TECHNICAL DATA

Colour Shades	RAL 7032 and RAL 7035 If ordered: RAL 1001, RAL 7001, RAL 7030 ja RAL 7038 Other colours: Agreed upon separately
Gloss	Semi-matt 4 (RT classification)
Coverage	Method 1: 0.5-1kg/m ² , dry film thickness 0.2 - 0.5mm Method 2: 1-1.6kg/m ² , dry film thickness 0.5-0.9mm. For waterproofing coating, use 1.6kg/m ² consumption Method 3: 2.0-2.5kg/m ² , additionally for example 0.5-1.5mm quartz sand approx. 1.5 kg/m ² . Total dry film thickness 1.5 – 2.0mm.
Can sizes	FACTORY READYMADE SHADE: 12 kg, 12.5 kg Not a base paint item: 12.5 kg
Thinner	Novofloor thinner (thinnable max 3 weight -%)
Application method	Spatula, mohair roller.
Drying time	Usably dry 24h Can be painted over 24h Fully hardened 7 days.
Density (kg/l)	1.6kg/l
Chemical resistance	Good
Abrasion resistance	Good
VOC	(cat A/i) 500g/l (2010) Novofloor 1-K Elastic N contains VOC max. 500g/l.
Storage	In a cool and dry place. The product reacts with moisture in the air and must be stored carefully in a sealed container. The storage time of the container if unopened, is 9 months. It is recommended that an opened container is used at once.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

NOVOFLOOR 1-K ELASTIC N

APPLICATION INSTRUCTIONS

Application conditions

The concrete surface should be dry and at least 4 weeks old. The relative humidity of the concrete should be less than 97%. During painting and drying, the air, the base and the paint must be between +10 and +30°C and the relative air humidity less than 80%.

On moist bases (relative humidity of the concrete > 97%) Temafloor 220W primer is used for priming according to the product insert.

Novofloor 1-K Elastic N can also be applied at lower temperatures ($\geq +3^{\circ}\text{C}$) when Novofloor Kiihdytin is added to the product (see product insert).

Surface preparation

New concrete floor:

The concrete adhesive layer is mechanically removed from the surface of the concrete, eg by sandblasting or diamond grinding. The best method for removal is chosen according to the space in question. After mechanical cleaning, the cement dust is carefully hoovered or washed off with water. Cement adhesive can also be removed with hydrochloric acid pickling. Pickling is made with diluted hydrochloric acid (1 part strong hydrochloric acid, 4 parts water). Then the floor is rinsed with plenty of water and dried well.

Old concrete floor:

The floor is cleaned of dust and loose debris. Grease, oil, chemicals and other impurities are removed by emulsion washing. Old and flaking paint is removed by sandblasting, grinding or milling. The best method for cleaning is chosen according to the space in question.

Floor holes are cleaned up all the way to a healthy and clean concrete. The cracks are opened, for example, with an angle grinder. Loose material and dust are removed.

Priming

Primer coating is done with Novofloor 1-K Primer Polyurethane Base thinned by 20-40% Novofloor Ohenne thinner. The primer is poured on the floor as a line and spread so abundant that the concrete surface is saturated. If needed, the priming treatment is done again undiluted to provide a non-porous surface.

The re-treatment is done immediately by "wet on wet" method. For moving on fresh varnish, spiked shoes are used. If the primer remains porous, it causes holes and air bubbles in the finished film.

Note! Pool gathering of Novofloor 1-K primer, for example at the bottom of a dripping groove must be avoided, because it causes bubbles on the primer and slows down the drying process.

Application

Treatment combinations

Method 1: Light usage (for example, glazed balcony), layer thickness 0.2-0.5mm

-Priming: 1-2 x Novofloor 1-K Primer (thinning 20-40%)

-Painting: 1 x Novofloor 1-K Elastic N

Method 2: Medium usage (for example, open balcony), layer thickness 0.5-0.9mm

-Priming: 1-2 x Novofloor 1-K Primer (thinning 20-40%)

-Coating: 1 x Novofloor 1-K Elastic N

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



NOVOFLOOR 1-K ELASTIC N

Method 3: Heavy usage with surface buffing (for example, outside corridor), layer thickness 1.5 -2.0mm

-Priming: 1-2 x Novofloor 1-K Primer (thinning 20-40%)

-Coating: 1 x Novofloor 1-K Elastic N + sanding full with quartz sand 0.5-1.5mm

-Painting: 1 x Novofloor 1-K Elastic N (thinning 3%)

Skirting/sloping surfaces:

-Coating/painting: 1 x Novofloor 1-K Elastic N + 1.5-2.0% Novofloor Paksunnin.

Non-slip buffing:

-In Methods 1 and 2, a buffing treatment may be used to increase the friction of the coating. A 12.5kg container of Tikkurila Liukeste is added and mixed thoroughly. The coating is poured on the floor in lines and evened out by cross rolling.

Mosaic flakes:

-In Methods 1 and 2, the surface can be livened up by sprinkling the desired color of Tikkurila Mosaic flakes 30-50g/m² on the surface.

Note! Mosaic flakes cannot be used with Method 3.

Cleaning of tools

Novofloor thinner.

Maintenance instructions

The painted surface reaches its final usage and chemical resistance about 1 week after the surface treatment. Avoid cleaning during this time. Clean the surface with a brush, mop or dusting cloth. Dirty surfaces can be cleaned with a neutral (pH 6-8) detergent moistened cleaning tool.

Note: Coffee, wine, tree/plant leaves, petals, etc. may cause discolouration of the surface. However, this does not affect the technical characteristics of the product.

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Danger. Flammable liquid and vapor. May cause an allergic skin reaction. Harmful if inhaled. May cause allergy or asthma symptoms or breathing difficulties if inhaled. Harmful to aquatic life with long lasting effects. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Do not breathe vapor. Avoid release to the environment. Wear protective gloves/clothing and eye/face protection. In case of inadequate ventilation wear respiratory protection. IF ON SKIN: Wash with plenty of soap and water. IF INHALED: Remove person to fresh air and keep comfortable for breathing. If experiencing respiratory symptoms: Call a POISON CENTER or physician. Contains isocyanates. May produce an allergic reaction. Contains: Carbonic acid, dimethyl ester, polymer with 1,6-hexanediol, 5-isocyanato-1-(isocyanatomethyl)-1,3,3-trimethylcyclohexane and 2-oxepanone, 1,6-hexanediyl-bis(2-(2-(1-ethylpentyl)-3-oxazolidinyl)ethyl)carbamate, 3-isocyanatomethyl-3,5,5-trimethylcyclohexyl isocyanate, oligomers, 2-ethylhexyl (6-isocyanatohexyl)-carbamate, hexahydromethylphthalic anhydride, isophorone diisocyanate, hexamethylene diisocyanate.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

NOVOFLOOR 1-K ELASTIC N



GHS02



GHS07




GHS08

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

NOVOFLOOR 1-K ELASTIC N


EN 1504-2:2004

	
1119	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
17	
TIK-A001-2017	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO2	sd > 50 m
Impact resistance	Class I: ≥ 4 Nm

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

NOVOFLOOR 1-K ELASTIC N

EN 13813:2002

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
17	
TIK-A002-2017	
EN 13813:2002	
Synthetic resin screed.	
Impact resistance	IR4

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.