



TIKKURILA
PRESTO LG
HIGH BUILD FILLER

- DESCRIPTION** Water-borne, ready to use high build filler. Filling ability 0-30 mm without cracking. Minimal shrinkage and good adhesion.
- RECOMMENDED USES** Interior walls and ceilings in dry premises.
- PRODUCT FEATURES** For leveling rough surfaces and filling holes on concrete and plaster surfaces. Light, easy to apply and sand. No need to finish with a finer filler.



PRESTO LG

TECHNICAL DATA	
Colour Shades	Grey
Can sizes	3 l, 10 l, 15 l
Thinner	Water, usually not thinned.
Application method	Apply with a smoothing trowel.
Drying time	The surface can be sanded and painted after the filler has dried completely (under normal conditions in 2–48 hours, depending on the layer thickness, temperature and the relative humidity of the air).
Density (kg/l)	0.9 kg/l, ISO 2811
Shrinkage	Minimal.
Volume solids (%)	46
Special feature	The light filling material used in this filler makes it light and easy to apply.
Storage	Must be protected from frost. Store in a dry and cool place, protected from sunlight. The opened container does not withstand long-term storage.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTO LG

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry. The minimum ambient temperature for use of the product is +10 °C and maximum relative air humidity 80%.

Surface preparation

Unpainted surfaces:

Clean the surfaces by removing any grease and dirt. Remove any dust and loose material by brushing.

Previously painted surfaces:

Wash previously painted surfaces with Maalipesu cleaning agent. Let the surface dry before further treatment. Remove as much loose paint as you can with a scraper and sand painted surfaces to a matte finish. Remove the sanding dust.

Application

Apply Presto LG with a smoothing trowel. Sand the dried surface and remove sanding dust. Apply another coat of filling if necessary.

Cleaning of tools

Clean tools with water.

Environmental protection and waste disposal


Deliver empty packaging and hardened mortar to a recycling point or waste tip according to local regulations.

Health and Safety

Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)).

PRESTO LG

EN 15824:2009

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5001b	
EN 15824:2009	
Internal plaster based on organic binder.	
Reaction to fire	B-s1,d0
Adhesion strength by pull off test	≥ 0,3 MPa
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.