



TIKKURILA
PRESTO R
ROLL-ON FILLER

DESCRIPTION

Water-borne, ready-to-use light filler for roller application. Filling capacity 3 mm without cracking and good adhesion on various substrates.

RECOMMENDED USES Interior walls and ceilings on dry premises.

PRODUCT FEATURES Especially suitable for filling the seams between gypsum boards and attaching sealing strips. For partial and complete leveling of wall and ceiling surfaces. Also suitable for spray application. For different substrates, such as gypsum board, concrete, light-weight concrete and rendered surfaces. Also suitable for plastering over old glass-fiber wall coverings.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTO R

TECHNICAL DATA

| | |
|---------------------------|--|
| Colour Shades | Color: close to white |
| Filling capacity | 3 mm without cracking. |
| Can sizes | 12 l |
| Application method | Application with roller, sprayer and steel trowel or automatic taper (bazooka). |
| Drying time | The surface can be sanded and painted in 2–24 hours, depending on the layer thickness, temperature and relative humidity of the air. |
| Density (kg/l) | 1.1 kg/l, ISO 2811 |
| Volume solids (%) | 55 |
| Grain size | Max. 0,15 mm. |
| Storage | Protect from frost. Badly closed or short cans endure badly long-time storage. |

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTO R

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry. The minimum ambient temperature for use of the product is +10 °C and maximum relative air humidity 80%.

Surface preparation

Unpainted surfaces:

Clean the surfaces of dirt. Brush off any dust and loose material. Level unpainted surfaces directly with Presto R filler for roller application.

Previously painted surfaces:

Wash previously painted surfaces with Maalipesu cleaning agent. Scrape off as much paint as you can and sand paint surfaces to a matte finish. Wipe the sanding dust off.

Application

Apply Presto R filler for roller application with a roller or spray gun and finish the surface with a trowel. Sand the dried surface and remove sanding dust. Apply another coat of filling if necessary.

Joint sealing

Spread the filler into the seam with a roller or spray gun. Immediately press the sealing strip into the wet filler with a smoothing trowel. Spread the filler over the sealing strip. Sand the dried surface smooth and remove the sanding dust. Finish the surface with a suitable Presto filler.

Cleaning of tools

Clean tools with water. Remove excess paint/ lacquer from tools and clean with water.

Environmental protection and waste disposal

Destroy unused product according to the local regulations for hazardous waste. Deliver empty packaging and hardened product to a recycling point or waste tip according to local regulations.


Health and Safety

Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: C(M)IT/MIT (3:1).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

PRESTO R


EN 13963:2005

| | |
|---|----------|
|  | |
| Tikkurila Oyj Kuninkaalantie 1 FI-01301 Vantaa Finland | |
| 2005 | |
| TIK-1650-5006a | |
| EN 13963:2005 | |
| Jointing material of gypsum plasterboards - Type 3A. | |
| Reaction to fire | A2-s1,d0 |
| Flexural strength | > 320 N |
| Release of dangerous substances | NPD |

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

PRESTO R

EN 15824:2009

| | |
|---|----------|
|  | |
| Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa Finland | |
| 2009 | |
| TIK-1650-5006b | |
| EN 15824:2009 | |
| Internal plaster based on organic binder. | |
| Reaction to fire | B-s1,d0 |
| Adhesion strength by pull off test | ≥ 0,3MPa |
| Release of dangerous substances | NPD |

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.