



TIKKURILA
PRESTONIT 5 + 5

DESCRIPTION Ready-to-use spray plaster. Fulfills the requirements of wear resistance category 04.

RECOMMENDED USES For partial and complete leveling of wall and ceiling surfaces.

PRODUCT FEATURES For priming and leveling interior ceiling and wall surfaces in dry conditions. Suitable for concrete, light-weight concrete, rendered, plaster, gypsum board and woodfiber board surfaces. Also suitable for previously painted surfaces. You can paint or apply wallpaper over the leveled surface.



PRESTONIT 5 + 5

TECHNICAL DATA	
Colour Shades	White
Coverage	On average 1 l/m ² with a plaster thickness of 1 mm. The required amount of depends on the surface.
Filling capacity	6 mm
Can sizes	14 l
Thinner	Water Usually not thinned.
Application method	Paste-spraying gun or steel trowel.
Drying time	Approximately two hours with a coating thickness of 1 mm. If you apply thicker coats, they will take longer to dry.
Density (kg/l)	1.5 kg/l, ISO 2811
Volume solids (%)	56
Grain size	Max. 0,30 mm.
Storage	Protect from frost.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTONIT 5 + 5

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry and the temperature at least +10 °C.

Surface preparation

Clean the surfaces by removing any grease and dirt. Remove any dust and loose material by brushing.

Application

Apply Prestonit 5+5 with a paste-spraying gun and smooth with a steel trowel. The plaster can also be applied manually.

Sand the surface when the plaster has dried. One or two applications will suffice under normal conditions.

The leveled surface can be painted, tiled or covered with plastic wallpaper.

Cleaning of tools

Clean tools with water.

Environmental protection and waste disposal


Deliver empty packaging and hardened mortar to a recycling point or waste tip according to local regulations.

Health and Safety

Wear protective gloves. Safety data sheet available on request. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)).

PRESTONIT 5 + 5


EN 15824:2009

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1620-5002b	
EN 15824:2009	
Internal plaster based on organic binder.	
Reaction to fire	B-s1,d0
Adhesion strength by pull off test	≥ 0,3 MPa
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

PRESTONIT 5 + 5

EN 13963:2005

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1620-5002a	
EN 13963:2005	
Jointing material of gypsum plasterboards - Type 2A.	
Reaction to fire	A2-s1,d0
Flexural strength	NPD
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.