

TIKKURILA

PROF EURO 20



PROF EURO 20 - EXTRA RESISTANT TO WASHING INTERIOR PAINT FOR DAMP PREMISES.

DESCRIPTION Professional extra resistant to washing waterborne interior paint.

RECOMMENDED USES Suitable for painting previously painted and unpainted walls and ceilings inside premises with

moderate and high humidity and with high maintenance such as: kitchen, bathroom, toilet, laundry, etc. on concrete, brick, plastered surfaces, filler-treated, gypsum plasterboard, particle board and wood-fiber plates, wallpaper for painting, suitable for painting radiators. Resistant to steam and condensation, protects against mold and fungus. Can be used in child welfare

institutions and facilities of the administrative group of medical institutions.

PRODUCT FEATURES Suitable for painting walls and ceilings inside premises with moderate and high humidity and with

high maintenance.



TECHNICAL DATA

Base paints A BASE, C BASE

Colour Shades Color cards:

Symphony Color System, Feel the Color, Feel the Color 2020, Deco Grey colour

card, Color Now 2022.

To tint in pastel and bright colors, use Tikkurila tinting service. Base A can also be used as white paint. Base C can be used only in tinted form. In case of painting in bright colors on the base C, it is recommended to apply a coat of base A paint, which

is colored in a similar shade first.

Gloss Semi-matt. SM

Coverage 9-12 m²/l on smooth non-absorbent surface;

6-8 m²/l on rough absorbent surface.

Can sizes A BASE: 0.9 I, 2.7 I, 5 I, 9 I

C BASE: 0.9 I, 2.7 I, 5 I, 9 I

Thinner Water

Application method Brush, roller or spray.

Drying time Drying time (20±2°C) and relative air humidity (65±5%): recoatable after 4 hours. The

specified level of stability of the coating to wash is achieved after 4 weeks.

Density (kg/l) Approx. 1,1-1,3 kg/l

Permeability to CO2 (EN

1062-6)

False

Wash resistance Excellent. Resistant to repeated washing with household non-abrasive detergents.

Wet scrub resistance SFS-EN 13300 class I, ISO 11998.

Volume solids (%) about 46% depending of the color.

VOC Contains VOC max. 30 g/l.





Storage	Protect from frost and direct sunlight. Store and transport in tightly closed containers at temperatures between +5°C and +25°C. Protect from the frost. Store and transport at temperature above 5 °C in tightly closed containers, protecting against moisture, heat and direct sunlight. Warranty storage period in unopened original package – 36 months.	



APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry and clean , the temperature at least 5°C and the relative humidity of the air not more than 80%.

Mixing components

If necessary, thinning with water no more than 5% by volume in case of application by brush or roller, no more than 10% by volume in case of application by spray.

Surface preparation

Unpainted surfaces:

Clean the unpainted surfaces of any dirt, dust and fat. Rough and absorbent surfaces is recommended to primed with primers Tikkurila Euro Primer or Tikkurila Prof Base. In case of continuous filler, no priming is required. Priming is mandatory before application onrough absorbent surfaces and surfaces filled with dry construction mixtures. Surfaces with mold, moss etc. are cleaned with Tikkurila Homeenpoisto in accordance with the instructions. When applied to radiators, pre-primed with Tikkurila Rostex primer.

Previously painted surface:

Remove any flaking, chalky and poorly adhering paint coats. Sand the surface, remove the sanding dust. Surfaces with mold, moss etc. are cleaned with Tikkurila Homeenpoisto in accordance with the instructions. Whitewash or lime paint completely removed, then clean the surface with water and detergent Tikkurila Maalipesu, after that washed with clean water and let it dry. Fill any holes and cracks and level the surfaces with filler Tikkurila Euro Filler or Euro Filler Light. Let the filler dry, sand the surfaces, remove the sanding dust and primed with primers Tikkurila Euro Primer or Tikkurila Prof Base

Painting

Stir the paint well before use. If necessary, thinning with water no more than 5% by volume in case of application by brush or roller, no more than 10% by volume in case of application by spray. Reserve enough paint from the same production batch for a uniform color of surface. Apply the paint in 2 coats.

Cleaning of tools

Clean tools with water. Clean tools with water.Remove lightly hardened paint with detergent Tikkurila Pensselipesu.

Maintenance instructions

If needed, after approx. 1 month from surface treatment, not the earliest. Clean the surfaces with a neutral (pH 6–8) washing solution with soft brush or soft sponge. Clean very dirty surfaces with a mild alkaline (pH 8–10) cleaning solution e.g. with soft brush or soft sponge. Wash off the solution with water using a sponge. After cleaning, the surface should not remain wet.

The surfaces must be handled with care for a few weeks, as the product will reach its final hardness and durability in about one month under normal conditions. If the surfaces need cleaning soon after the surface treatment, cleanlightly by using a soft brush or a damp cloth.

About the Google Translate Community
About GoogleRules and Guidelines Help Submit a Review





About the Google Translate Community
About GoogleRules and Guidelines Help Submit a Review

About the Google Translate Community

About GoogleRules and Guidelines Help Submit a Review





About the Google Translate Community
About GoogleRules and Guidelines Help Submit a Review

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.