



TIKKURILA  
**SISÄ 2**



- DESCRIPTION** Water-borne dispersion paint for interior use.
- RECOMMENDED USES** Wall and ceiling surfaces in dry interior spaces.
- PRODUCT FEATURES** For priming of concrete, plaster, filler, plasterboard, and wood fiberboard surfaces according to instructions.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

## SISÄ 2

TECHNICAL DATA	
<b>Base paints</b>	AP BASE
<b>Colour Shades</b>	Light shades can be tinted in Tikkurila colors. Color accuracy can differ from the sample.
<b>Gloss</b>	Full matt. (6/RT classification)
<b>Coverage</b>	Absorbent surfaces 3 - 5 m <sup>2</sup> /l. Non-absorbent surfaces 7 - 9 m <sup>2</sup> /l.
<b>Can sizes</b>	2.7 l, 9 l, 18 l
<b>Thinner</b>	Water
<b>Application method</b>	Brush, roller or spray. Airless spray application - nozzle 0.018" - 0.023" - thinning 0-10 % by volume.
<b>Drying time</b>	Dust dry in half an hour. Recoatable after 1-2 hours.
<b>Density (kg/l)</b>	Approx. 1.4 kg/l, SFS 3635.
<b>Chemical resistance</b>	Resists cleaning chemicals and weak solvents, such as white spirit.
<b>Heat resistance</b>	85 °C, SFS 3757.
<b>Volume solids (%)</b>	30
<b>VOC</b>	(cat A/a) max. 30g/l (2010). Sisä 2 contains VOC max. 30g/l.
<b>Storage</b>	Protect from frost.



# SISÄ 2

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be painted must be dry, the temperature at least +5°C and the relative humidity of the air below 80%.

### Surface preparation

Unpainted surfaces:

Clean the surfaces by removing any dirt and dust. If needed, fill the surfaces with a suitable filler and sand the dried surface. Remove the sanding dust.

Previously painted surfaces:

Wash the surfaces with diluted paint cleaning agent and rinse carefully with water. Fill cracks and holes with a suitable filler and sand the dried surface. Remove the sanding dust.

### Painting

Stir Sisä 2 well before use and thin with water, if necessary. Apply 1-2 coats with a roller, brush, or spray.

### Cleaning of tools

Clean tools immediately after use with water. Remove excess paint/ lacquer from tools and clean with water.

### Maintenance instructions

If needed, approx. 1 month after painting at the earliest:

The surfaces are preferably dry-cleaned by using a vacuum cleaner, soft brush or dust towel. Damp cleaning can leave marks on the surface, especially on dark shades.

### Maintenance treatment

Surfaces painted with Sisä 2 can be maintenance painted with the same or similar water-borne paint. See Pretreatment.

### Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

### Health and Safety

Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.