

Temabond WG 300

DESCRIPTION

A two-component, low temperature curing modified epoxy paint.

PRODUCT FEATURES AND RECOMMENDED USES

- Forms a tight coat with good chemical and abrasion resistance.
- Good adhesion also to wire-brushed steel.
- Recommended for repairing of damages caused by transport or installation and for repainting and touch-up painting of earlier painted surfaces.
- Can also be applied on old alkyd paint surfaces.
- Especially used as a primer for steel surfaces difficult to clean in process and chemical industry and in water immersion, such as ship hulls and ballast tanks.

TECHNICAL DATA

Volume solids 70±2% (ISO 3233)

Weight solids 80±2%

Specific gravity 1.3 kg / l (mixed)

Mixing ratio
Base 1 part by volume Temabond WG 300
Hardener 1 part by volume 008 7519

Pot life (+23°C) 1 hour

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
wet	dry	
145µm	100µm	7.0 m²/l
290µm	200µm	3.5 m²/l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 150µm	- 5°C	0°C	+5°C	+10°C	+23°C
Dust dry, after	18h	14h	6½h	3½h	2½h
Touch dry, after	48h	36h	17h	9h	5h
Recoatable, after	48h	36h	17h	9h	5h
Recoatable with epoxy, max. without sanding	2 months	2 months	2 months	2 months	2 months
Recoatable with polyurethane, after	-	-	14d	14d	14d

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Gloss

Semi-gloss.

Color shades

Temaspeed Premium tinting.

Temabond WG 300

APPLICATION INSTRUCTIONS

Surface preparation	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Remove rust by tool cleaning to minimum St2 or blast clean to Sa2 or Sa2½. Blast clean to grade Sa2½ for immersion. (ISO 8501-1).</p> <p>Earlier painted surfaces: Roughen old paint surfaces using e.g. abrasive wheel, sandpaper or blast cleaning.</p>
Recommended primers	Temabond WG 300, Temabond WG 200.
Recommended topcoats	Temacoat GPL, Temacoat GPL-S MIO, Temacoat GPL-S Primer, Temacoat GS 50, Temacoat RM 40, Temadur 10, Temadur 20, Temadur 50, Temadur 90, Temadur HB 50, Temadur HB 80, Temathane 50, Temathane 90, Temathane PC 50, Temathane PC 80, Temacryl EA 50, Temabond WG 300, Temabond ST 300.
Application conditions	<p>All surfaces must be clean, dry and free from contamination. The temperature of the ambient air and the surfaces should not fall below -5°C during application and drying. The temperature of the paint should be at least +15°C. Relative humidity of the air should not exceed 80% during application and drying. The surface temperature of steel should remain at least 3°C above the dew point. Good ventilation and sufficient air movement is required in confined areas during application and drying.</p> <p>Note! There is a natural tendency of this coating to chalk, discolor or yellow unevenly. It is recommended to use polyurethane topcoat when there are high aesthetic requirements on color appearance.</p>
Mixing components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use power mixer for mixing. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface and weaken the properties of the coating.
Application	<p>For airless spraying, the product is thinned 0–10%. Recommended nozzle tip is 0.013"–0.019" and pressure 120–180 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For brush application product should be thinned according to the circumstances.</p>
Thinners	Thinner 1031
Cleaning of equipment	Thinner 1031
VOC	<p>The Volatile Organic Compounds amount is 280 g/litre of paint.</p> <p>VOC content of the paint mixture (thinned 10% by volume) is 340 g/l.</p>
HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.</p> <p>A health and safety data sheet is available on request from Tikkurila Oyj.</p> <p>For industrial and professional use only.</p>



Temabond WG 300

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.