

# Temamatt Matting Paste

## DESCRIPTION

A matting paste.

## PRODUCT FEATURES AND RECOMMENDED USES

- Flattens the gloss of Temalac FD 80, Temalac ML 90, Duasolid 50, Temadur 90, Diccoplast 30, Diccoplast 80 and Dicco Flex 30.

## TECHNICAL DATA

### Specific gravity

1.0 kg / l

### Directions for use

After addition of Temamatt Matting Paste stir the paint very thoroughly (using e.g. carousel mixer or hand drill with paddle) so that Temamatt Matting Paste is well mixed.

The gloss values in the table below are guiding values. Variations may occur. Film thickness, drying conditions and application method may affect on the gloss.

Note! Temamatt Matting Paste will reduce the viscosity of certain products.

### Flattening effect

Products for metal:

Product	Amount/l	Temamatt Matting Paste amount/l	Gloss Gardner 60°
Duasolid 50 white	6	0.5	50
		1	35
		2	20
Temadur 90 white	7.5	1	85
		2	55
Temalac FD 80 white	9	0.5	60
		1	35
		2	15
Temalac ML 90 white	9	0.5	70
		1	45
		2	20

Products for wood:

Product	Code	Gloss with amount of Temamatt by weight		
		2.5%	5.0%	7.5%
Diccoplast 30, TAL	754 7221	20	15	10
Diccoplast 80, TAL	634 7221	65	50	40
Dicco Flex 30, TAL	752 7221	20	15	10

The amount of the Temamatt is calculated to paint amount without acid and thinner. Add Temamatt with stirring effectively. Add acid and thinner after Temamatt.



# Temamatt Matting Paste

## APPLICATION INSTRUCTIONS

**VOC** The Volatile Organic Compounds amount is 760 g/litre of paste.

**HEALTH AND SAFETY** Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.  
A health and safety data sheet is available on request from Tikkurila Oyj.

### **For industrial use only.**

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.