



TIKKURILA

TIXOMATT

SPECIAL PRIMER FOR INTERIOR WALLS AND CEILINGS / FULL-MATT

DESCRIPTION

Thixotropic covering and isolating alkyd primer for interior walls and ceilings.

RECOMMENDED USES

Walls and ceilings.

PRODUCT FEATURES

For new and previously painted plaster, filler-treated, chipboard, wood fiberboard and wooden surfaces. For interior use only.

TIXOMATT

TECHNICAL DATA

Colour Shades	White. Not tintable.
Gloss	Full matt.
Coverage	10–12 m ² /l.
Can sizes	1 l, 3 l, 10 l, 20 l
Application method	Roller, spray or brush. Airless spraying – nozzle 0.013"–0.018" (0.330–0.460 mm).
Drying time	Dust dry after 1 hour. Recoatable the following day. Please note, primer contains organic solvents with a noticeable odor which may occur during painting and drying process. Good ventilation is recommended
Density (kg/l)	1.6 kg/l, ISO 2811
Volume solids (%)	55
VOC	(cat A/g) 350g/l (2010) Tixomatt contains max. 350 g/l of VOC.
Storage	Unaffected by cold storage or transportation. Badly closed or short cans endure badly long-time storage.

TIXOMATT

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry, the ambient temperature at least +5 °C and the relative humidity of air below 80%.

Surface preparation

Unpainted surfaces:

Clean the surface of any dirt and dust.

Previously painted surfaces:

Wash the surfaces with Maalipesu detergent and let dry well.

Application

Tixomatt does not usually need to be stirred or thinned before use.

If needed, e.g. for priming, thin 5–10% with Alkydiohenne 2010. After thinning, allow the paint to stand for approx. 1 hour to restore its gelatinous texture.

Apply 1–2 coats by roller, spray or brush.

Finish with topcoat, if needed (e.g. Siro Himmeä, Harmony or Joker)

The product contains organic solvents with a noticeable odor.

Cleaning of tools

Clean tools with White Spirit 1050 or Tikkurila Pensselipesu (Tool Cleaner). Remove excess paint/ lacquer from tools and clean with water.

Maintenance instructions

If needed, after approx. 1 month from painting, at the earliest: Clean the surface with a neutral (pH 6–8) dish washing solution and a soft brush, sponge or cleaning cloth. Clean soiled surfaces using mild alkaline (pH 8–10) detergent solution and a cloth, mop or sponge. Rinse the surface carefully.

The product achieves its final hardness and durability after one month under normal conditions, therefore the surfaces must be handled with care during a couple of weeks. If the surfaces need to be cleaned soon after finishing, clean them lightly with a soft brush or damp cleaning cloth.

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Warning. Flammable liquid and vapor. May cause drowsiness or dizziness. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Avoid breathing vapor. Use only outdoors or in a well-ventilated area. **Warning!** Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

TIXOMATT



GHS02

GHS07

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.