



TIKKURILA

PRESTO LV

HUMID-ROOM FILLER

DESCRIPTION

Water-borne, ready to use light filler for wet rooms. Filling ability 4 mm with no cracking. Minimal shrinkage and good adhesion.

RECOMMENDED USES

For wall and ceiling surfaces in wet rooms, e.g. leveling bathroom walls and ceilings before attaching the plastic cover, tiling or painting.

PRODUCT FEATURES

For the full or partial leveling of gypsum and woodfiber board, concrete and rendered surfaces in wet rooms. Especially suitable for attaching sealing strips and use as a filler in wet rooms.



PRESTO LV

TECHNICAL DATA

Colour Shades	Blue-gray
Can sizes	3 l, 10 l
Application method	Apply with a smoothing trowel.
Drying time (23°C and 50% relative air humidity)	The surface can be sanded after the filler has dried; under normal conditions in 2–24 hours, depending on the layer thickness, temperature and relative humidity of the air. The surface can be painted, tiled or covered after the filling has dried completely.
Density (kg/l)	1.1 kg/l, ISO 2811
Shrinkage	Minimal.
Volume solids (%)	61
Special feature	The light filling material used in this filler makes it light and easy to apply.
Storage	Protect from frost. Badly closed or short cans endure badly long-time storage.

PRESTO LV

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry. The minimum ambient temperature for use of the product is +10 °C and maximum relative air humidity 80%.

Surface preparation

Unpainted surfaces:

Clean the surfaces by removing any grease and dirt. Remove any dust and loose material by brushing. Level unpainted surfaces directly with Presto LV Märkätilatasoite.

Previously painted surfaces:

Wash surfaces with Maalipesu cleaning agent. Allow the surface to dry. Remove as much paint as you can and sand painted surfaces to a matte finish. Remove the sanding dust.

Application

Apply Presto LV Märkätilatasoite with a smoothing trowel. Sand the dried surface and remove sanding dust. Apply another coat of filling if necessary.

Cleaning of tools

Clean tools with water.

Environmental protection and waste disposal


Deliver empty packaging and hardened mortar to a recycling point or waste tip according to local regulations.

Health and Safety

Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

PRESTO LV

EN 13963:2005

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5004a	
EN 13963:2005	
Jointing material of gypsum plasterboards - Type 3A.	
Reaction to fire	A2-s1,d0
Flexural strength	> 320 N
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

PRESTO LV

EN 15824:2009

CE	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5004b	
EN 15824:2009	
Internal plaster based on organic binder.	
Reaction to fire	B-s1,d0
Adhesion strength by pull off test	≥ 0,3 MPa
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.