



TIKKURILA

## PRESTONIT V

### DESCRIPTION

Ready-to-use spray plaster. Fulfills the requirements of wear resistance category 05.

### RECOMMENDED USES

For partial and complete leveling of wall and ceiling surfaces.

### PRODUCT FEATURES

For priming and leveling interior ceiling and wall surfaces in damp conditions. Suitable for concrete, light-weight concrete, rendered, plaster, gypsum board and woodfiber board surfaces. Also suitable for previously painted surfaces. The surface can be painted, tiled or covered with plastic wallpaper.



# PRESTONIT V

## TECHNICAL DATA

<b>Colour Shades</b>	Light blue
<b>Coverage</b>	On average 1 l/m <sup>2</sup> with a plaster thickness of 1 mm. The required amount of depends on the surface.
<b>Filling capacity</b>	Max. thickness 2.0 mm, depending on the conditions.
<b>Can sizes</b>	14 l
<b>Thinner</b>	Water  Usually not thinned.
<b>Application method</b>	Paste-spraying gun or steel trowel.
<b>Drying time (23°C and 50% relative air humidity)</b>	Approximately one hour with a coating thickness of 1 mm. If you apply thicker coats, they will take longer to dry.
<b>Density (kg/l)</b>	1.7 kg/l, ISO 2811
<b>Volume solids (%)</b>	64
<b>Grain size</b>	Enint. 0.20 mm.
<b>Storage</b>	Protect from frost.

# PRESTONIT V

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be treated must be dry and the temperature at least +10 °C.

### Mixing components

Does not usually require dilution.

### Surface preparation

Clean the surfaces by removing any grease and dirt. Remove any dust and loose material by brushing.

### Application

Apply Prestonit V spray plaster with a paste-spraying gun and smooth with a steel trowel. The plaster can also be applied manually.

Sand the surface when the plaster has dried. One or two applications will suffice under normal conditions.


The leveled surface can be painted, tiled or covered with plastic wallpaper.

### Cleaning of tools

Clean tools with water.

# PRESTONIT V

EN 13963:2005

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
TIK-1620-5003a	
EN 13963:2005	
Jointing material of gypsum plasterboards - Type 2A.	
Reaction to fire	A2-s1,d0
Flexural strength	NPD
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

# PRESTONIT V

EN 15824:2009

CE	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1620-5003b	
EN 15824:2009	
Internal plaster based on organic binder.	
Reaction to fire	B-s1,d0
Adhesion strength by pull off test	≥ 0,3 MPa
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.