



TIKKURILA

SUPI LATTIAÖLJY

PROTECTIVE OIL FOR WOODEN FLOORS IN WET ROOMS

DESCRIPTION

A water-borne wood oil emulsion for humid interior spaces, based on natural oil derivatives. Protects wood against moisture and dirt and decreases cracking of wood surfaces.

RECOMMENDED USES Wooden floors and duckboards.

PRODUCT FEATURES Suitable for bare wood or previously oil-treated surfaces in humid premises. Also suitable for thermally modified wood and hardwood.



SUPI LATTIAÖLJY

TECHNICAL DATA

Base paints	EC BASE
Colour Shades	Color cards: Interior wood stains and lacquers colour card, Timeless translucent. Can be tinted in Tikkurila translucent colors.
Coverage	8-15 m ² /l, depending on the porosity of the wood surface and the type of wood.
Can sizes	0.9 l
Application method	Application with brush or sponge.
Drying time	Touch-dry after a few hours. Ready for use after approximately 2 days. The porosity of the substrate and the amount of oil used affect the drying time.
Density (kg/l)	1.0 kg/l, ISO 2811.
Volume solids (%)	14
Storage	Close can carefully for next use. Badly closed or short cans and/or tinted products do not withstand long storage. Tinted products should be used during the same painting season. Protect from frost

SUPI LATTIAÖLJY

APPLICATION INSTRUCTIONS

Application conditions

During treatment and drying, the temperature of the air, surface and wood stain must be at least +5 °C, and the relative humidity of the air less than 80%.

Surface preparation

New clean wood surfaces:

Clean the wood surface of any dirt and dust. Wet the surface lightly with water spray, let dry and sand off the loose wood fibers that have risen with a roughness of 230. Remove the sanding dust.

Surfaces treated previously with wood oil:

Wash with Supi Saunapesu cleaning agent according to instructions, rinse thoroughly and let dry. Sand if necessary and remove the sanding dust. Remove loose material with a scraper and/or wire brush. If a visible film remains on the surface, remove it before treatment.

Application

Stir Supi Floor Oil thoroughly before use and during application.

Apply once with a brush or sponge, pressing it down tightly so that all oil is absorbed evenly into the wood. Wipe off any excess oil after approx. 30 min. Spread evenly along the entire length of the board in continuous strokes to avoid overlapping. Oil treatment makes the wood look darker.

Pre-heat and ventilate the sauna thoroughly before use.

Carry out maintenance when necessary. Surfaces exposed to continuous moisture stress need retreatment at intervals.

Cleaning of tools

Clean the tools with water and soap Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint. Clean the tools with water and soap Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

Handle new surface with care for approximately 1 week. The surface can be cleaned lightly with a soft brush or mop after approximately two days from the surface treatment, if necessary.

The surface can be cleaned at the earliest after 1 month with Supi Sauna Clean (1-2 dl detergent into 5 liters of water) to allow the product to achieve its final hardness and durability.

Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.



SUPI LATTIAÖLJY

Health and Safety

Harmful to aquatic life with long lasting effects. Avoid release to the environment. Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)) and 2-octyl-2H-isothiazol-3-one (OIT). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.