



Temadur Accelerator

DESCRIPTION Accelerator solution which makes the curing faster.

PRODUCT FEATURES AND RECOMMENDED USES

- Facilitates early taping of painted surfaces
- Not suitable for Temadur HB polyurethane paints
- Used to accelerate the curing of Temadur 20, 50 and 90 polyurethane paints and Temadur Clear varnish

TECHNICAL DATA

Specific gravity 0.9 kg / l

Influence on drying times

Amount of accelerator, +23°C	0%	5%	10%
Pot life	4h	1h	½h
Tapeable	24h	8h	4h

Directions for use Max. 10 vol.-% of the amount of the paint/hardener mixture.



Temadur Accelerator

APPLICATION INSTRUCTIONS

Application Mix the base and the hardener. Add the required amount of accelerator. Thin with Thinner 1048, if necessary, and mix thoroughly. Pay attention to the shortened pot life and start the painting work without delay.

HEALTH AND SAFETY Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

For industrial use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.