

Temafloor AC610 Clear

DESCRIPTION A two-component, solvent-free acrylic topcoat.

- PRODUCT FEATURES AND RECOMMENDED USES**
- Suitable for topcoating of Temafloor AC509 and Temafloor AC501 acrylic screeds
 - Especially for hard mechanical abrasion in dry interior premises
 - Excellent resistance to abrasion and scratches
 - Good resistance to chemicals
 - Suitable for dry indoor premises, such as corridors, retail stores, changing rooms etc

TECHNICAL DATA

Volume solids approx. 100%

Specific gravity 0.99 kg /l (ready made mixture)

Mixing ratio

Temperature (°C)*	The amount of hardener (percentage of weight of the binder)	Pot life (min)	Drying time (min)
+10	1.5	ab. 25	ab. 45
+20	1.5	ab. 15	ab. 35
+25	1.0	ab. 12	ab. 25
+30	1.0	ab. 8	ab. 15

* Temperature of the binder, air and the floor.

Possible hardeners BP-50-FT, Perkadox®CH-50 or PEROXAN BP-Pulver 50 W.

Practical coverage Coverage is on the average:
 Topcoat 1.5–3.3 m²/l
 Practical coverage depends on the porosity and evenness of the surface and on the application method.

Cleaning of equipment Thinner 006 1400 or Temafloor AC Clean.

Finish Gloss. Sunlight will affect on the shade and the gloss of the varnish in the long run.

Colors Clear

Thinning instructions Do not thin.

VOC VOC 2004/42/EC (cat A/j), 500 g/l (2010).
 Temafloor AC609 Clear: max. VOC < 500 g/l.

Can sizes 20,0 L, 200,0 L

Temafloor AC610 Clear

APPLICATION INSTRUCTIONS

- Surface preparation** Always remove all grease, oil, and other impurities with Maalipesu detergent before grinding. Remove laitance or old peeling paint layers by power grinding, milling, or vacuum grit blasting. Choose the method best suited for the premises. Clean out pot holes removing all loose or brittle material. Open cracks with e.g. an abrasive tool. After mechanical pre-treatment remove all loose material and dust carefully with a vacuum cleaner.
The substrate must have a tensile strength above 1.5 MPa. For application on cementitious leveling screed: check compatibility with the leveling screed manufacturer.
- Application conditions** The relative humidity of the concrete should not exceed 97%. Residual moisture content should be below 4 weight-%. The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 80%.
- Mixing components** First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 2 minutes to get homogenous mixture) by using a low speed industrial hand drill with a paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.
- Topcoating** Topcoating can be carried out after the screed has cured. Pour the varnish mixture onto the floor, apply with a rubber trowel and level with a roller. Observe a right amount of hardener. Using excessive amounts of hardener can cause yellowing and may weaken the properties of the topcoat. Film thickness should be 0.3–0.7 mm. Thicker film causes yellowing of the surface.

HEALTH AND SAFETY Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

For professional use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.


In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

Temafloor AC610 Clear

EN 1504-2:2004

The European harmonized product standard EN 1504-2:2004 defines the requirements for surface protection systems for concrete.

This product is tested and CE-labelled in accordance with the tables 1d, 1f and 1g in the appendix ZA.

	
0809	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA	
14	
0809-CPD-0773	
TIK-1600-5008	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO ₂	$s_D > 50 \text{ m}$
Impact resistance	Class I: $\geq 4 \text{ Nm}$
Capillary absorption and permeability to water	$w < 0,1 \text{ kg/m}^2 \cdot h^{0,5}$
Abrasion resistance	$< 3000 \text{ mg}$
Reaction to fire	E_{fl}
Adhesion strength by pull off test	$\geq 2,0 \text{ N/mm}^2$
Permeability to water vapour	Class III, $s_D > 50 \text{ m}$
Resistance to severe chemical attack	Class I

Tested as part of a system together with Temafloor AC 102 Primer and Temafloor AC 509.