

Temazinc 77

DESCRIPTION

A two-component, polyamide cured zinc rich epoxy paint.

PRODUCT FEATURES AND RECOMMENDED USES

- Contains over 80% zinc and fully meets the requirements of the standard ISO 12944-5 for zinc-rich primers. The primer provides good cathodic protection for steel
- Used in coating systems where extended durability is required
- Used as a primer in epoxy, polyurethane, acrylic and chlorinated rubber systems for steel surfaces exposed to severe climatic conditions
- Can be used without a topcoat on surfaces exposed to weathering
- Recommended for bridges, cranes and steel frameworks as well as steelwork and equipment in the forest and chemical industries, such as tubular bridges, conveyors etc

TECHNICAL DATA

Volume solids 52±2% (ISO 3233)

Specific gravity 2.0 kg / l (mixed)

Mixing ratio Base 3 parts by volume Temazinc 77
Hardener 1 part by volume 008 7440

Pot life (+23°C) 16 hours

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
wet	dry	
75µm	40µm	13.0 m²/l
155µm	80µm	6.5 m²/l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 40µm	+5°C	+10°C	+23°C	+35°C
Dust dry, after	50min	20min	10min	5min
Touch dry, after	2h	1h	30min	15min
Recoatible, after	5h	3h	1h	30min

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Gloss Matt.

Color shades Grey

Temazinc 77

APPLICATION INSTRUCTIONS

Surface preparation	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) In order to get the best performance the surface profile should be medium grit. (ISO 8503-2)</p>
Recommended topcoats	<p>Temacoat GPL-S Primer, Temacoat GF Primer, Temacoat GPL-S MIO, Temacoat GS 50, Temacoat RM 40, Temacoat HB 30, Temachlor 40, Temacryl AR 50, Temanyl MS Primer, Temacoat Primer, Temacoat SPA 50, Temacoat 50, Temabond ST 200, Temabond ST 300, Fontecoat EP 50 Beige, Temacoat HS-F Primer.</p>
Application conditions	<p>All surfaces must be clean, dry and free from contamination. The temperature of the ambient air, surface and paint should not fall below +5°C during application and drying. Relative humidity of the air should not exceed 80% during application and drying. The surface temperature of steel should remain at least 3°C above the dew point. Good ventilation and sufficient air movement is required in confined areas during application and drying.</p> <p>Note! There is a natural tendency of this coating to chalk, discolor or yellow unevenly. It is recommended to use polyurethane topcoat when there are high aesthetical requirements on color appearance.</p>
Mixing components	<p>First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use power mixer for mixing. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface and weaken the properties of the coating.</p>
Application	<p>For airless spraying, the product is thinned depending on the temperature of the components and shape of the object approximately 0–5%. Agitate during application. Recommended nozzle tip is 0.015"–0.021" and pressure 120–180 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For brush application product should be thinned according to the circumstances.</p> <p>Sharp edges, corners, weld seams and other areas difficult to cover properly by spray application should be coated by brush before the spray application.</p>
Thinners	<p>Thinner 1031</p>
Cleaning of equipment	<p>Thinner 1031.</p>
VOC	<p>The Volatile Organic Compounds amount is 480 g/litre of paint.</p> <p>VOC content of the paint mixture (thinned 5% by volume) is 495 g/l.</p>
HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.</p> <p>A health and safety data sheet is available on request from Tikkurila Oyj.</p> <p>For industrial use only.</p>



Temazinc 77

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.